

INFORMATIONAL PROPOSAL (For information only, not to be used for bidding)

NEBRASKA DEPARTMENT OF ROADS
LETTING DATE: December 04, 2014

CALL ORDER: 600 CONTRACT ID: 6975D

CONTROL NO./SEQ. NO.: 60975D /000 PROJECT NO.: S-80-3(1058)

TENTATIVE START DATE: 06/29/15 CONTRACT TIME: 85 WORKING DAYS

LOCATION: I-80, ROSCOE - PAXTON, PHASE 2
IN COUNTY: KEITH

BIDDER

GROUP 3 CONCRETE PAVEMENT

NOTES

THE TOTAL AMOUNT OF WORK WHICH WILL BE ACCEPTED IN
THIS LETTING IS LIMITED TO \$_____.

THE NUMBER OF _____ CONTRACTS WHICH WILL BE
ACCEPTED IN THIS LETTING IS LIMITED TO _____.

NOTICE TO ALL BIDDERS

To report bid rigging activities, call: 1-800-424-9071

The U.S. Department of Transportation (DOT) operates the above toll-free “hotline” Monday through Friday, 8:00 a.m. to 5:00 p.m. eastern time. Anyone with knowledge of possible bid rigging, bidder collusion, or other fraudulent activities should use the “hotline” to report such activities.

The “hotline” is part of the DOT’s continuing effort to identify and investigate highway construction contract fraud and abuse and is operated under the direction of the DOT Inspector General. All information will be treated confidentially and caller anonymity will be respected.

LETTING QUESTIONS

Prior to the letting, any questions pertaining to the Special Provisions or the Plans for this project should be submitted to NDOR in a written format through the Bid Express (BidX) website at <https://www.bidx.com/ne/lettings>. Likewise, NDOR will post answers exclusively to the BidX website. All official answers will be identified as “Authorized by NDOR.” **Questions will not be answered verbally.**

STATE OF NEBRASKA
DEPARTMENT OF ROADS

Required Provisions Supplemental to the

Standard Specifications for Highway Construction

I. Application

These contract provisions shall apply to all work performed on the contract by the contractor with his own organization and with the assistance of workmen under his immediate superintendence and to all work performed on the contract by piecework, station work, or by subcontract.

The contractor shall insert in each of his subcontracts all of the stipulations contained in the Special Provisions and these Required Provisions.

A breach of any of the stipulations contained in these Required Provisions may be grounds for termination of the contract.

II. Equal Opportunity

1. **Selection of Labor**

During the performance of this contract, the contractor shall not discriminate against labor from any other state.

2. **Nebraska Fair Employment Practices Act**

The contractor shall not discriminate against any employee or applicant for employment, to be employed in the performance of this contract with respect to his hire, tenure, terms, conditions, or privileges of employment, because of his race, color, religion, sex or national origin. The contractor agrees to post in a conspicuous place or places a notice to be provided by the State Highway Department which sets forth excerpts of the Act.

3. **Nebraska Equal Pay Act**

The contractor shall not discriminate on the basis of sex by paying wages to employees of one sex at a lesser rate than the rate paid to employees of the opposite sex for comparable work on jobs which have comparable requirements. An abstract of the Act is included on the notice which is provided by the State Highway Department.

April 4, 1995

III. Employment of Labor

1. General

No person under the age of sixteen (16) years, and no one whose age or physical condition is such as to make his employment dangerous to his health or safety, or to the health and safety of others shall be employed on any project. This paragraph shall not be construed to deny the employment of older people or physically handicapped persons, otherwise employable, where such persons may be safely assigned to work which they can ably perform.

No person currently serving sentence to a penal or correction institution shall be employed on any project.

Except as specifically provided under this section, workers who are qualified by training or experience to be assigned to projects of this character shall not be discriminated against on any grounds whatsoever.

2. Payrolls

Payrolls and basic records relating thereto will be maintained during the course of the work and preserved for a period of three years thereafter for all laborers and mechanics working on the site of the work.

The contractor's and subcontractor's payroll records shall be available for inspection by authorized representatives of the State Highway Department and authorized representatives of Federal Agencies.

The wages of labor shall be paid in legal tender of the United States, except that this condition will be considered satisfied if payment is made by a negotiable check, on a solvent bank, which may be cashed readily by the employee in the local community for the full amount, without discount or collection charges of any kind. Where checks are used for payment the contractor shall make all necessary arrangements for them to be cashed and shall give information regarding such arrangements.

No fee of any kind shall be asked or accepted by the contractor or any of his agents from any person as a condition of employment on the project.

No laborers shall be charged for any tools used in performing their respective duties except for reasonably avoidable loss or damage thereto.

Every employee on the work covered by this contract shall be permitted to lodge, board and trade where and with whom he elects and neither the contractor nor his agents, nor his employees shall directly or indirectly require as a condition of employment that an employee shall lodge, board or trade at a particular place or with a particular person.

No charge shall be made for any transportation furnished by the contractor or his agents to any person employed on the work.

April 4, 1995

No individual shall be employed as a laborer on this contract except on a wage basis, but this shall not be construed to prohibit the rental of teams, trucks or other equipment from individuals. No such rental agreement, or any charges for feed, gasoline, supplies, or repairs on account of such agreement, shall cause any deduction from the wages accruing to any employee except as authorized by the regulations hereinbefore cited.

IV. Safety and Accident Prevention

In the performance of this contract, the contractor shall comply with all applicable Federal, State and local laws governing safety, health and sanitation. The contractor shall provide all safeguards, safety devices and protective equipment and take any other needed actions, on his own responsibility or as the contracting officer may determine, reasonably necessary to protect the life and health of employees on the job and the safety of the public and to protect property in connection with the performance of the work covered by the contract.

V. Subletting or Assigning the Contract

The contractor shall perform with his own organization contract work amounting to not less than 30 percent of the total contract amount except that any items designated in the contract as "Specialty Items" may be performed by subcontract and the amount of any such "Specialty Items" so performed may be deducted from the total contract amount before computing the amount of work required to be performed by the contractor with his own organization.

Any items that have been selected as "Specialty Items" for the contract are listed as such in the Special Provisions found elsewhere in the contract.

No portion of the contract shall be sublet, assigned, or otherwise disposed of except with the written consent of the contracting officer or his authorized representative. Requests for permission to sublet assign or otherwise dispose of any portion of the contract shall be in writing and accompanied by a showing that the organization which will perform the work is particularly experienced and equipped for such work. The contractor shall give assurance that the minimum wage for labor as stated in his proposal shall apply to labor performed on all work sublet, assigned or otherwise disposed of in any way. Consent to sublet, assign or otherwise dispose of any portion of the contract shall not be construed to relieve the contractor of any responsibility for the fulfillment of the contract.

April 4, 1995

**SPECIAL PROVISIONS
FOR
STATE
PROJECT NO. S-80-3(1058)**

GENERAL CONDITIONS

Bids for the work contemplated in this proposal form will be received at the office of the Nebraska Department of Roads in Room 104 of the Central Office Building at 1500 Highway 2 at Lincoln, Nebraska, on December 4, 2014, until 1:30 P.M.

- a. Bids submitted by mail should be addressed to the Nebraska Department of Roads, c/o Contract Lettings Section, P.O. Box 94759, Lincoln, NE 68509-4759.
- b. Bids submitted electronically over the internet, shall be submitted using www.bidx.com.

The 2007 Edition of the Standard Specifications for Highway Construction, including all amendments and additions thereto effective at the date of the contract, are made a part of these Special Provisions, through reference.

The Required Provisions dated April 4, 1995, are attached to and are a part of this proposal form.

The attention of bidders is directed to the Required Provisions covering subletting or assigning the contract.

The proposal contains a statement that the contractor is complying with, and will continue to comply with, fair labor standards in the pursuit of his business and in the execution of the work contemplated in this proposal.

Fair labor standards shall be construed to mean such a scale of wages and conditions of employment as are paid and maintained by at least fifty per cent of the contractors in the same business or field of endeavor as the contractor filing this proposal.

STATUS OF UTILITIES

The following information is current as of October 22, 2014

Aerial and/or underground utilities may exist within the limits of this project. The Contractor shall determine to their satisfaction the extent of occupancy of any utility facilities located within the project construction areas and the extent of conflict with the proposed work under this contract.

At this time, no utilities have been required to relocate their facilities.

Any utility adjustments or interruption of service for the convenience of the Contractor shall be the sole responsibility of the Contractor.

To arrange for utilities to locate and flag their underground facilities, contact The Diggers Hotline of Nebraska at 1-800-331-5666 or dial 811.

Any work necessary will be concurrent with construction.

STATUS OF RIGHT-OF-WAY

All necessary right-of-way has been acquired.

SPECIAL PROSECUTION AND PROGRESS (Holidays)

The Contractor will be required to schedule his operations in a manner to have all traffic lanes open to traffic on the following holidays:

- Memorial Day and Labor Day weekends – these holiday weekends shall begin at 3:00 p.m., Friday, and shall include the remainder of Friday and all day Saturday, Sunday and the Monday holiday.
- July 4th - If July 4th falls on a Monday or Friday, the Saturday and Sunday either preceding or following July 4th shall be included as part of the holiday.
- If July 4th falls on either Tuesday, Wednesday or Thursday, only that day will be considered as the holiday.
 - If July 4th falls on a Saturday or Sunday, the day preceding and the day following July 4th shall be included as part of the holiday.
 - The July 4th holiday shall begin at 3:00 p.m. on the day preceding the first day of the July 4th holiday, as defined above.

Failure to have all traffic lanes open to traffic, as specified, on these holidays will result in a liquidated damage assessment of \$5,000 per day. This assessment will be in addition to other liquidated damages described elsewhere in this proposal or in the Standard Specifications used for this project.

SPECIAL PROSECUTION AND PROGRESS (General Requirements)

The following requirements shall apply to this project.

1. The maximum lane closure length, excluding tapers, will be limited to 6.0± miles. The Contractor will be allowed two lane closures in each direction, with a minimum distance of 3.0± miles between the lane closures, or as otherwise directed by the Engineer.
2. With the exception of holidays, there are no peak hours on this project. However, if, in the opinion of the Engineer, a lane closure is not being utilized for construction purposes, the Engineer shall notify the Contractor to remove the lane closure and the Contractor shall have one hour to remove the lane closure after the notification..
3. The Contractor shall have a work crew at the closure site at all times during a lane closure during daylight hours, unless otherwise described elsewhere in this proposal.
4. Lane closures shall be limited to the length required for the work being performed, up to a maximum length of 6.0± miles.

Although the Department will not unreasonably prevent the Contractor from utilizing a lane closure of the maximum length, lane closures shall not be established for lengths greater than necessary. The Contractor is directed to schedule the placement of traffic control devices to accommodate each day's closure to the extent practical. Accordingly, the Department will only pay for those traffic control devices considered reasonably necessary to protect the actual work area.

5. A lane closure shall not be installed during nighttime hours. Nighttime hours shall be defined as being from sunset to ½ hour after sunrise in the eastbound direction and from ½ hour before sunset to sunrise in the westbound direction.
6. NDOR personnel shall require approximately 8-10 days, with Contractor provided traffic control for the concrete pavement repair marking. This work shall be performed during daylight hours prior to the start date of the project and without the charge of working days. During this period, the maximum lane closure length may be exceeded, as directed by the Engineer. NDOR personnel will require 4 set-ups, two in each direction (one to mark the driving lane/outside shoulder, and then one for the passing lane/inside shoulder).
7. When traffic is reduced to a single lane in either direction, the Contractor shall be required to maintain a minimum 12 foot lane width for through traffic at all times during those operations.

**SPECIAL PROSECUTION AND PROGRESS
(Optional Concrete Protection Barriers)**

1. It will be the Contractor's option to use concrete protection barriers on this project.
2. Concrete protection barriers shall only be used for the listed in the following Table, unless otherwise allowed by the Engineer.

Beginning Station	Ending Station	Lane
2401+50.	2403+37.5	EB D&PL
2467+55.	2468+20.	EB D&PL
2205+57.	2208+07.	EB D&PL
1997+50.	2005+00.	EB D&PL
2073+24.	2080+74.	EB D&PL
2148+24.	2155+74.	EB D&PL

EB D&PL = Eastbound Driving and Passing Lane

- a. Repair work behind the Concrete protection barriers shall be performed on consecutive working days starting immediately after the barriers are in place.
- b. The Concrete protection barriers shall be removed or relocated once the concrete in the repair has attained strength and can be opened to traffic.

- c. Lane rental fees may be charged for failure to perform the repair work on consecutive working days or to remove or relocate the concrete protection barriers as described.
3. The items “Concrete Protection Barriers,” “Relocate Concrete Protection Barriers,” “Inertial Barrier System”, “Relocate Inertial Barrier System” and “Replacement Module” will be measured and paid for as defined in Section 422.04 and 422.05 of the Standard Specifications.
4. If the Contractor does not plan to utilize concrete protection barriers or inertial barrier systems, or to relocate concrete protection barriers, they shall bid the items:
- Concrete Protection Barriers,
 - Relocate Concrete Protection Barriers,
 - Inertial Barrier System,
 - Relocate Inertial Barrier System, and
 - Replacement Module
- at unit prices of \$0.00 for each. If the Contractor bids these items at \$0.00 and later decides to utilize them, it will be at the Contractor’s expense.
5. No change orders will be approved to increase the cost of “Concrete Protection Barriers,” “Relocate Concrete Protection Barriers,” “Inertial Barrier System”, “Relocate Inertial Barrier System” or “Replacement Module” items after award of the contract.

**SPECIAL PROSECUTION AND PROGRESS
(Assessments)**

As described in paragraph No. 2 in the provision titled **SPECIAL PROSECUTION AND PROGRESS (General Requirements)**, the Contractor’s failure to have a lane closure removed within one hour after notification from the Engineer shall result in the assessment of a \$80 per lane per hour per closure internal liquidated damage assessment per lane closure. This assessment shall begin at the start of the second hour after notification from the Engineer and it shall continue per hour until, and including, the hour the lane closure(s) is removed and the lane is open to traffic. If multiple lane closures are involved in the notification, this assessment shall apply to each lane closure. This assessment has not been provided for in the contract and shall be in addition to other liquidated damages that are part of the contract. The following formula was used to determine this assessment:

$$\begin{aligned}
 \text{Cost} &= [(1-\%T)(\text{AHT})(\$ \text{Pass}) + (\%T)(\text{AHT})(\$ \text{Trucks})] \times D \\
 &= [(1-0.51)(551)(\$0.23) + (0.51)(551)(\$0.44)] \times 0.43 \\
 &= [\$62.10 + \$123.65] \times 0.43 \\
 &= \$79.87 \rightarrow \text{Rounded to } \$80/\text{lane}/\text{hour}/\text{closure}
 \end{aligned}$$

Where: %T = percent trucks = 51%
 AHT = average hourly traffic = 551
 \$ Pass = passenger car factor = \$0.23
 \$ Trucks = truck factor = \$0.44
 D = delay (in minutes)

ENVIRONMENTAL COMMITMENT

Below are the Conservation Conditions that will be required for this project. All conditions and regulations of any permit obtained for this project will be followed by the Contractor.

To avoid unanticipated impacts:

- The Contractor shall not stage, store waste or stockpile materials and equipment in undisturbed locations, or in known/potential wetlands and/or known/potential streams that exhibit a clear "bed and bank" channel. Potential wetland areas consist of any area that is known to pond water, swampy areas or areas supporting known wetland vegetation (e.g., Cattails, bulrush, Canary reed grass, smartweed, or areas where there is a distinct difference in vegetation (at lower elevations) from the surrounding upland areas.)

To avoid impacts to the community:

- Emergency services shall be given adequate notice of any closures.

To avoid Hazardous Material concerns:

- Any items that may contain hazardous materials must be properly handled and disposed of as outlined in the Standard Specifications.

SPECIAL PROSECUTION AND PROGRESS (Migratory Birds) (A-42-1112)

The Department of Roads will, to the extent practicable, schedule the letting of projects such that clearing and grubbing can occur outside of the primary nesting season in Nebraska which has been determined to generally occur between April 1 and September 1. Work on structures, such as but not limited to bridges and culverts, should occur outside the primary swallow nesting season, April 15 to September 30, unless approved methods of avoiding nesting have been taken on the bridge and/or culvert structures. The nesting dates above are a guide only, nesting can occur outside of those dates. Work outside of those dates is not exempt from compliance with the Migratory Bird Treaty Act.

The Contractor shall, to the extent possible, schedule work on structures, such as but not limited to bridges and culverts, and clearing and grubbing activities to occur outside the primary nesting season in Nebraska. However, if circumstances dictate that project construction or demolition must be done when nesting migratory birds may be present, a survey of the number of active nests and species of birds shall be conducted by qualified personnel representing the Contractor, and assisted by the Project Manager (PM), NDOR Environmental Section staff, or the United States Department of Agriculture (USDA) Animal and Plant Health Inspection Service (APHIS) - Wildlife Services Office. If the survey finds that nests will be impacted by the proposed construction, the Contractor may be responsible for delays.

The following guidance is provided for compliance with the Migratory Bird Treaty Act for construction of NDOR projects:

1. The Contractor shall submit a plan to the NDOR regarding how he intends to accomplish bridge demolition or clearing and grubbing of the project to avoid conflict with nesting migratory birds.
2. The Contractor must submit a temporary erosion control plan tailored to fit the plan for clearing and grubbing.
3. If construction operations result in unavoidable conflict with nesting migratory bird's eggs or young, which will result in "taking" nests and their contents, the Contractor should notify the NDOR Project Manager (PM). The PM shall notify the Environmental Section of Planning and Project Development by telephone at 402-479-4766.
4. The NDOR Environmental Section will then determine if assistance in conducting the survey will be provided by the NDOR Environmental Section (if available) or from the USDA APHIS - Wildlife Services Office and arrange for assistance with the survey of nest numbers, bird species, etc. Results of the survey shall be maintained by the NDOR until project completion.
5. If the nesting survey is required, and the project was awarded prior to the nesting season, and the Contractor did not accomplish clearing/grubbing and/or work on bridge/culvert structures outside the nesting season, the Contractor will reimburse the Department of Roads for each survey required at \$1,000 per survey. If the project was awarded during the nesting season, and construction activities are such that clearing/grubbing and/or work on bridge/culvert structures must be accomplished prior to any other activity on the project, then there will be no charge assessed for the initial survey. The Contractor is responsible for removing all trees surveyed, that do not contain active nests, and for taking appropriate measures on bridge/culvert structures, within 3 days of the survey. Reimbursement for additional surveys may be charged if the Contractor fails to remove the trees within 3 days of the survey, and requires an additional survey. Survey reimbursement will be determined on a project specific basis, considering the project timeline and associated activities.
6. If an active nest is found during the survey, the Contractor should do everything possible to restructure his activities and leave the nest undisturbed until the young fledge. Fledging could occur within a week, or up to a month, after the survey depending on the species of bird and whether the nest contained eggs or young. Also depending on the species of bird and their sensitivity to disturbance, a buffer of up to 30 feet surrounding the tree with the active nest could be required.
7. If construction cannot be rescheduled to allow the birds to fledge, and it is determined as an unavoidable "take" circumstance, the Contractor shall stop all work within 30 feet of the active nest and coordinate with the Construction Project Manager to determine how to proceed. The Construction Project Manager will then coordinate with the NDOR Environmental Section and they will facilitate coordination with the US Fish and Wildlife Service and the Federal

Highway Administration (for projects using Federal-aid) to determine the appropriate way to address the active nest. No work shall occur within 30 feet of the active nest until US Fish and Wildlife Service coordination is complete and the requirements of the Migratory Bird Treaty Act are satisfied.

8. It is the Contractor's responsibility to schedule his work to accommodate the process of conducting a survey(s) and submitting the necessary documentation if avoidance is not practicable. The Contractor shall be responsible for using any legal and practical method to prevent the nesting of birds in order to prevent the need for any survey and prevent the need for additional surveys. It is understood and agreed that the Contractor has considered in the bid all of the pertinent requirements concerning migratory birds (including endangered species) and that no additional compensation, other than time extensions if warranted, will be allowed for any delays or inconvenience resulting in these requirements.

STORM WATER DISCHARGES (A-43-0408)

In compliance with the Federal Water Pollution Control Act, authorization to discharge storm water on this project has been granted under National Pollutant Discharge Elimination System (NPDES) General NPDES Permit Number NER110000 for Storm Water Discharges from Construction Sites to Waters of the State of Nebraska. This permit became effective on January 1, 2008.

Contractors are advised that, under the Construction Storm Water General Permit, ***plant sites, camp sites, storage sites, and borrow or waste sites not shown on the plans may be subject to separate NPDES permit authorization requirements for stormwater discharges from those locations.*** Contractors shall be responsible for verifying the need for NPDES permit coverage with the Nebraska Department of Environmental Quality (NDEQ). When required for these locations, the filing of a "Notice of Intent" shall be made by the Contractor directly to the NDEQ.

Additionally, asphalt (SIC Code 2951) or concrete (SIC Code 3273) batch plants that are owned by a private contractor and are operated on a contract-for-service basis to perform work for the Contractor completing the project may be subject to NPDES General Permit Number NER000000 for Industrial Storm Water Discharges. While the plant may be required for completion of the project, it is not under the control of the Department (or other project owner); and the filing of a "Notice of Intent" shall be made by the Contractor directly to the NDEQ.

The NDEQ may be contacted at 402-471-4220 for additional information.

**REQUIRED SUBCONTRACTOR/SUPPLIER QUOTATIONS LIST
(A-43-0307)**

All bidders must provide to the NDOR the identity of all firms who provided quotations on all projects, including both DBEs and non-DBEs. This information must be on a form provided by the NDOR Contracts Office.

If no quotations were received, the bidder must indicate this in the space provided.

Each bidder will be required to submit one list per letting to cover all projects bid.

**PROPOSAL GUARANTY BID BOND
(A-43-0307)**

Paragraphs 1.a. and 1.b. of Subsection 102.15 in the *Standard Specifications* are void and superseded by the following:

- a. OPTION 1 - (Project Specific Paper Bid Bond). The Bid Bond shall be executed on an original Department Bid Bond Form, which may be obtained from the Department. The original Bid Bond shall be delivered to the Department with the bid. A reproduction or a copy of the original form will not be accepted and will cause the bid not to be opened and read.
- b. OPTION 2 - (Annual Bid Bond). The Department at its discretion may allow a bidder to place an "Annual Bid Bond" on file with the Department. This bond would cover all projects the bidder bids for a 12-month period shown in the bond. The bidder must indicate in the bid submittal to the Department that their "Annual Bid Bond" applies to the submitted bid. The original Annual Bid Bond shall be executed on the Department of Roads Bid Bond Form, which may be obtained from the Department. A reproduction or a copy of the original form will not be accepted.

**WORKER VISIBILITY
(A-43-0507)**

Pursuant to Part 634, Title 23, Code of Federal Regulations, the following modified rule is being implemented:

Effective on January 1, 2008, all workers within the right-of-way who are exposed either to traffic (vehicles using the highway for purposes of travel) or to construction equipment within the work area shall wear high-visibility safety apparel.

High-visibility safety apparel is defined to mean personal protective safety clothing that:

- 1 - is intended to provide conspicuity during both daytime and nighttime usage, and
- 2 - meets the Performance Class 2 or Class 3 requirements of the ANSI/ISEA 107-2004 publication titled "American National Standards for High-Visibility Safety Apparel and Headwear."

VALUE ENGINEERING PROPOSALS (VEP)
(A-43-0807)

Subsection 104.03 in the *Standard Specifications* is amended to include the following:

14. A VEP will not be accepted if the proposal is prepared by an Engineer or the Engineering Firm who designed the contract plans.

LEGAL RELATIONS AND RESPONSIBILITY TO THE PUBLIC
(A-43-0210)

Paragraph 4.a. of Subsection 107.01 in the *Standard Specifications* is void and superseded by the following:

4. a. Whenever the Contractor violates any governing Federal, State or Local environmental quality regulation and/or is in noncompliance with any environmental commitment, the violating activity must cease immediately until the appropriate remedy can be determined by: the Engineer, the NDOR Environmental Section, the Federal Highway Administration (for projects utilizing Federal-aid) and other agencies, as deemed appropriate. The Engineer, with assistance from the NDOR Environmental Section and the FHWA, will provide a written order confirming the appropriate corrective action to the Contractor. Work can resume to normal conditions once the Engineer determines that the violation or non-compliance has been addressed in accordance with the order for corrective action.

Subsection 107.01 in the *Standard Specifications* is amended to include the following two paragraphs:

5. Should the Contractor encounter any previously unidentified hazardous materials, the Engineer shall be promptly notified. The Contractor shall suspend operations in the area involved until such time that arrangements are made for their proper treatment or removal.
6. The Contractor shall prevent the transfer of invasive plant and animal species. The Contractor shall wash equipment at the Contractor's storage facility prior to entering the construction site. The Contractor shall inspect all construction equipment and remove all attached vegetation and animals prior to leaving the construction site.

**SPECIAL PROSECUTION AND PROGRESS
(Federal Immigration Verification System)
(A-43-1209)**

The Contractor shall register with and use a Federal Immigration Verification System to determine the work eligibility status of newly hired employees physically performing services within the State of Nebraska. The Prime Contractor shall contractually require every subcontractor to register with and use a Federal Immigration Verification System to determine the work eligibility status of newly hired employees physically performing services within the State of Nebraska.

The Federal Immigration Verification System shall be an electronic verification of the work authorization program of the Illegal Immigration Reform and Immigration Responsibility Act of 1996, 8 U.S.C. 1324a, known as the E-Verify Program. The Contractor may use an equivalent Federal program designated by the United States Department of Homeland Security or other Federal agency authorized to verify the work eligibility status of a newly hired employee. The equivalent program shall comply with the Immigration Reform and Control Act of 1986.

The Prime Contractor shall furnish a letter to the NDOR Construction Division in Lincoln on company letterhead and signed by an officer of the company stating that documentation is on file certifying that the Contractor and all subcontractors have registered with and used a Federal Immigration Verification System. The Contractor shall maintain all records of registration and use for a period of three years and make records available upon request. The Contractor shall contractually require subcontractors to maintain all records for a period of three years and make records available upon request.

Payment will not be made to the Contractor for using the Federal Immigration Verification System or the maintenance of the records. This work shall be subsidiary to the work being performed.

The Contractor's Certification shall become part of the final records of the Contract. The Department considers this document to have direct bearing to the beginning interest date and may affect the amount of interest earned.

**CONTRACT TIME ALLOWANCE
(A-43-0911)**

Paragraph 5. of Subsection 108.02 of the *Standard Specifications* is void and superseded by the following:

5. Each week, the Engineer shall post on the Department's website a report of working days or calendar days charged. The Contractor then has 14 days from the day the Engineer's report is posted to provide a written explanation of why he/she does not concur with the working days or calendar days as assessed.

Paragraph 6.b. of Subsection 108.02 of the *Standard Specifications* is amended to include the following:

- (4) If the time allowance for the contract has been established on a calendar day basis, the Contractor is expected to schedule the work and assign whatever resources are necessary to complete the work in the time allowance provided regardless of the weather. Accordingly, regardless of anything to the contrary contained in these *Specifications*, the Department will not consider delays caused by inclement or unseasonable weather as justification for an extension of the contract time allowance unless:
 - i. the weather phenomena alleged to have contributed to or caused the delay is of such magnitude that it results in the Governor issuing a Disaster Declaration, **and**
 - ii. the weather phenomena alleged to have contributed to or caused the delay can clearly be shown to have directly impacted the work on the critical path identified on the Contractor's schedule.

Paragraphs 10.b. and 10.c. of Subsection 108.02 of the *Standard Specifications* are void and superseded by the following:

- b.
 - (1) If the extra work is not in the original contract, time extensions will be granted by determining the actual time necessary to accomplish the extra work.
 - (2) If the extra work is the result of the addition of additional quantities of existing contract items, time extensions will be granted by either:
 - (i) determining the actual time necessary to accomplish the extra work; or
 - (ii) determining the additional time to be granted by comparing the value of the additional quantities of work to the total amount of the original contract when measurement of the actual additional time is not possible or practical.
 - (3) In either case, only the time necessary to perform the extra work of the additional quantities of existing contract items when the extra work or the additional quantities of existing contract items are deemed to be the current controlling operation will be granted as a time extension.
- c. Increases in quantities of work associated with traffic control items measured by the day will not be considered for extending the contract time allowance. Overruns of traffic control items that are measured by methods other than time may be considered for extending the contract time allowance, but they must be deemed to be a controlling operation when the overrun of quantities occurs.

**PARTIAL PAYMENT
(A-43-1110)**

Paragraph 2. of Subsection 109.07 of the *Standard Specifications* is void and superseded by the following:

2. When the value of the work completed during a semi-monthly period exceeds \$10,000, the Contractor will receive semi-monthly progress estimates from which the Department shall make such retentions as may be allowed by the contract, provided that the nature and quality of the completed work are satisfactory and provided further that the progress of the work conforms to the requirements of Subsection 108.07.

Paragraph 3.b. of Subsection 109.07 of the *Standard Specifications* is void and superseded by the following:

- b. Under normal circumstances, the Department shall not retain any earnings on a progress estimate. However, the Department reserves the right to retain such amounts as are necessary for material deficiencies, anticipated liquidated damages, unpaid borrow, and for other reasons to protect the Department's interests.

**PARTIAL PAYMENT
(A-43-0611)**

Paragraph 4. of Subsection 109.07 of the *Standard Specifications* is void and superseded by the following:

4. a.
 - (1) Upon presentation by the Contractor of receipted bills, billing invoices, or such other documentation sufficient to satisfy the Engineer and verify the Contractor's or subcontractor's actual costs for the materials, payments may also be allowed for acceptable nonperishable materials purchased expressly to be incorporated into the work and delivered in the vicinity of the project or stored in acceptable storage places within Nebraska.
 - (2) Materials not delivered and stored in the immediate vicinity of or on the actual project site must be clearly marked to identify the project on which they are to be used, must be segregated from similar materials at the storage site, and cannot be included in a supplier's inventory of material available for sale for other purposes.
 - (3) All items eligible for partial payment as stored materials must be available for verification, sampling, and measurement.
- b. The amount to be included in the payment will be determined by the Engineer, but in no case shall it exceed 100 percent of the value of the materials documented. This value may not exceed the appropriate portion of the value of the contract item or items in which such materials are to be incorporated, nor

shall the quantity in any case exceed the total estimated quantity required to complete the project.

- c. Payment will not be approved when the documented value of such materials amounts to less than \$1,000.00, when the progress of the work is not in accordance with the requirements set forth in Subsection 108.07, or when the material can reasonably be expected to be incorporated into the work and eligible for payment as completed work on a progress estimate within 15 days of being placed into storage.
- d. Deductions at rates and in amounts which are equal to the payments will be made from estimates as the materials are incorporated into the work.
- e. Payment for the materials shall not in itself constitute acceptance, and any materials which do not conform to the specifications shall be rejected in accordance with Subsection 106.05.
- f. The Contractor shall be responsible for all damages and material losses until the material is incorporated into the work and the work is accepted.
- g. Partial payment will not include payment for fuels, supplies, form lumber, falsework, other materials, or temporary structures of any kind which will not become an integral part of the finished construction.
- h. No partial payments will be made on living or perishable plant materials until planted.

**BUY AMERICA
(A-43-0212)**

Subsection 106.07 in the *Standard Specifications* is void and superseded by the following:

106.07 -- Buy America

- 1. The Buy America rule requires that steel or iron materials be produced domestically, and only those products which are brought to the construction site and permanently incorporated into the completed project are covered. Construction materials, forms, etc., which remain in place at the Contractor's convenience, but are not required by the contract, are not covered.
- 2. To further define the coverage, a domestic product is a manufactured steel construction material that was produced in one of the 50 States, the District of Columbia, Puerto Rico, or in the territories and possessions of the United States.
- 3. All manufacturing processes to produce steel or iron materials (i.e., smelting, and any subsequent process which alters the steel or iron material's physical form or shape, or changes its chemical composition) must occur within one of the 50 States, the District of Columbia, Puerto Rico, or in the territories and possessions of the United States, to be considered of domestic origin. This includes processes such as casting, rolling, extruding, machining, bending, grinding,

drilling, and coating. Coating includes epoxy coating, galvanizing, painting, and any other coating that protects or enhances the value of the material. The manufacturer shall include a statement on the material test report or certification that all material described above except the coating material is a domestic product.

4. Raw materials used in the steel or iron materials may be imported. All manufacturing processes to produce steel or iron materials must occur domestically. Raw materials are materials such as iron ore, limestone, waste products, etc., which are used in the manufacturing process to produce the steel products. Waste products would include scrap; i.e., steel no longer useful in its present form from old automobiles, machinery, pipe, railroad tracks and the like. Also, steel trimmings from mills or product manufacturing are considered waste. Extracting, crushing, and handling the raw materials which is customary to prepare them for transporting are exempt from Buy America. The use of pig iron and processed, pelletized, and reduced iron ore manufactured outside of the United States may be used in the domestic manufacturing process for steel and/or iron materials.
5. Notwithstanding this requirement, a minimum of foreign steel or iron materials will be permitted if its value is less than one-tenth of one percent of the total contract cost or \$2,500, whichever is greater.
6. Upon completion of all work utilizing steel or iron products, the Prime Contractor shall furnish a letter to the State on company letterhead and signed by an officer of the company stating that documentation is on file certifying that all steel or iron materials brought to the construction site and permanently incorporated into the work complied in all respects with the Buy America requirements.

BORROW, WASTE, STOCKPILE, AND PLANT SITE APPROVAL (A-43-0512)

Subsection 107.02 in the Standard Specifications is amended to include the following:

4. Site Approval:
 - a. When borrow is obtained from a borrow site or waste excavation is placed at sites which are not shown in the contract, or the Contractor plans to use a plant or stockpile site which is not shown in the contract, the Contractor shall be solely responsible for obtaining all necessary site approvals. The Department will provide the procedures necessary to obtain approvals from the U.S. Army Corps of Engineers, U.S. Fish and Wildlife Service, Nebraska State Historical Society, Nebraska Game and Parks Commission, and Nebraska Department of Natural Resources on the NDOR website. The Contractor shall also be responsible for obtaining a Discharge Number from the Nebraska Department of Environmental Quality (NDEQ) that allows work under the current Construction Stormwater Permit. The Contractor shall also be responsible for obtaining any and all other permits required by local governments.

- b. It is anticipated that it may require 60 calendar days or more for the Contractor to obtain the necessary approvals. The Contractor will not be allowed to begin work at borrow or waste sites until the necessary approvals are obtained. No extension of completion time will be granted due to any delays in securing approval of a borrow or disposal site unless a review of the time frames concludes that there were conditions beyond the Contractor's control.

Paragraph 7. of Subsection 205.02 in the Standard Specifications is void and superseded by the following:

- 7. Borrow and Waste Site Approval:
 - a. Borrow and waste site approvals shall be in accordance with Section 107.02.
 - b. Material shall not be removed from borrow sites until preliminary cross sections and representative soil samples have been taken by the Engineer. The Contractor shall notify the Engineer a sufficient time in advance of the opening of any borrow site so that cross sections may be taken.
 - c. Material shall be removed in a manner that will allow accurate final cross sections to be taken for determining the quantity of excavation. The surfaces of the borrow sites shall be bladed and shaped to drain as shown in the contract or as directed by the Engineer.

**SPECIAL PROSECUTION AND PROGRESS
(Subletting or Assigning of Contract)
(A-43-0414)**

Subsection 108.01 in the Standard Specifications is void and superseded by the following:

108.01 – Subletting or Assigning of Contract

- 1. a. (1) The Contractor will not be allowed to sublet, assign, sell, transfer, or otherwise dispose of any portion of the contract or any right, title, or interest therein; or to either legally or equitably assign any of the money payable under the contract or the claims without the prior written consent of the Engineer.
- (2) With the Engineer's consent, the Contractor may sublet up to 70 percent of the work.
- (3) Any items designated in the contract as "specialty items" may be performed by subcontract.

- (4) The cost of any subcontracted "specialty items" may be deducted from the total contract cost before computing the percentage of work required to be performed by the Contractor.
 - (5) Subcontracts, or transfer of contract, will not release the Contractor of any liability under the contract and bonds.
 - b. Certain items of work may be performed without a subcontract. A list of items not requiring a subcontract is available from the Engineer.
2. The performance of any work by a subcontractor before the date of authorization by the Department shall subject both the Contractor and subcontractor to the imposition of appropriate sanctions by the Department.
3. a. The Contractor's request to sublet work shall be made electronically to the NDR Construction Engineer using project management software identified by the Department. A signed subcontract agreement shall be on file in the Contractor's office when the request is made. The subcontract agreement must provide that the subcontracted work will be completed according to the terms of the contract. The required and Special Provisions contained in the proposal shall be physically included in any subcontract.
 - b. On all Federal-aid projects, a scanned copy (.pdf format) of the signed subcontract agreement shall be included with the subcontracting request. (Federal-aid projects can be identified by inclusion in the Proposal of Form FHWA-1273 (REQUIRED CONTRACT PROVISIONS FEDERAL-AID CONSTRUCTION CONTRACTS)).**
 - c. Scanned copies (.pdf format) of all executed subcontracts, written agreements, and/or lease agreements used to meet DBE goals shall be submitted to the NDR Construction Engineer with the subcontracting request. These copies must show labor cost, material prices, overhead and profit.
4. a. Second tier subcontracts will be allowed.
 - b. If a DBE firm subcontracts work to another firm, only work subcontracted to another DBE firm can be counted toward meeting a DBE goal.
 - c. All requests for second tier subcontracting shall be submitted to and approved by the Prime Contractor before they are forwarded to the NDR Construction Engineer for approval.
5. All subcontract documents relating to the contract shall be maintained during the course of the work and preserved for a period of three years thereafter. These documents shall be available for inspection by authorized representatives of State and Federal agencies. Scanned copies (.pdf format) of the signed subcontract agreements not specifically identified elsewhere in this Subsection shall be furnished to the Department upon request.
6. The Contractor may discuss a proposed subcontract with the Engineer before entering into a signed subcontract agreement, but final approval will not be

granted until a formal request and proper certification has been received by the Department.

7. On projects requiring submittal of certified payrolls, all subcontractor payrolls shall be checked by the Contractor before submittal to the Engineer.
8. a. The Prime Contractor, and subcontractors when subletting work to lower tier subcontractors, shall include language which can be identified as a "Prompt Payment Clause" as a part of every subcontract for work and materials.
 - b. (1) The language constituting the "Prompt Payment Clause" will require payment to all first tier subcontractors for all labor and materials --- for work completed to date --- within 20 calendar days of receipt of progress payments from the Department for said work. Similar language in a contract between a subcontractor and a lower-tier subcontractor will require payment to the lower tier subcontractor for all labor and materials --- for work completed to date --- within 10 calendar days of receipt of progress payments from the prime Contractor for said work.
 - (2) The language constituting the "Prompt Payment Clause" will also stipulate the return of retainage within 30 calendar days after the satisfactory completion of the work by the subcontractor as evidenced by inclusion of the work on a progress payment.
 - (3) Additionally, the language constituting the "Prompt Payment Clause" may stipulate the subcontractor's obligation to return to the Contractor or subcontractor, as the case may be, any overpayments which result from adjustments to measured and recorded quantities as part of the preparation of subsequent progress payments or the final records. Overpayments shall be returned to the Prime Contractor or subcontractor, as the case may be, within 20 calendar days of receiving notice of the adjusted quantities and the amount of the overpayment.
- c. The Prime Contractor of subcontractors, as the case may be, may withhold payment only for just cause and shall not withhold, delay, or postpone payment without first receiving written approval from the Department.
- d. (1) The failure by the Prime Contractor to abide by the agreements identified in the "Prompt Payment Clause" without just cause, including the timely return of retainage, is a material breach of this contract which may result in the Department withholding the amount of payment from the prime Contractor that should have been paid to the subcontractor, termination of this contract, or other such remedy as the Department deems necessary.
 - (2) Additionally, the failure of any subcontractor to abide by the agreements identified in the "Prompt Payment Clause" without just cause, including the timely return of retainage to lower tier subcontractors, or by failing to return overpayments in a timely manner when the language permitted in Paragraph 8.b.(3) above is included in the subcontract may result in the Department withholding subcontract approval for other work until the overpayments have been returned.

9. a. (1) For Davis Bacon (DBRA)-covered projects and Non-DBRA-covered projects, a Contractor or subcontractor may wish to use another individual owner-operator or trucking company to supplement his or her hauling fleet. (The Department will not recognize multiple individuals claiming to be collectively identified as a single "owner operator.")
- (2) This supplemental individual or company must either become a subcontractor (first tier or lower tier, as the case may be) or be otherwise documented by the utilizing Contractor or subcontractor by entering into a lease agreement for the trucks and showing the driver (or drivers) from the supplemental company on the Prime Contractor's or subcontractor's payrolls in the manner described below.
- (3) Payrolls will only be accepted from the Prime Contractor or approved subcontractors.
- b. (1) If the decision is made to subcontract the hauling, the Prime Contractor must first notify the NDOR Construction Office to request subcontract approval. As part of the subcontract approval process --- at any tier --- the proper certificates of insurance must be provided before approval will be granted.
- (2) Additionally, on DBRA-covered projects, the Prime Contractor must submit payrolls for all subcontractors --- at any tier.
- c. (1) Owner/Operators of trucks hired by a Contractor or subcontractor to supplement his or her hauling fleet are not subject to Davis Bacon wage requirements. However, they must still be shown on a payroll prepared by the Contractor or subcontractor for whom they are working with the notation "owner/operator."
- (2) Any other employees of the "owner/operator" must appear on the certified payroll in complete detail and must be compensated according to the wage rates established for the project.
- d. In the event a Prime Contractor or subcontractor elects to not subcontract the supplemental driver or drivers but instead chooses to "carry the workers/truckers on their payroll," the following requirements must be met:
 - (1) The Prime Contractor's or subcontractor's certified payroll must contain the names of all workers/truck drivers, and the payroll should identify their supervisors (including "owner-operators").
 - (2) Pay checks for the workers/truckers in question must be drawn against the Prime Contractor's or subcontractor's payroll or other account.
 - (3) Owner/Operators need only be identified as such on the payroll. Additional drivers, if any, from the "owner-operator's" company must appear on a payroll in complete detail and be compensated according to the wage rates established for the project.

- (4) The Prime Contractor or subcontractor must enter into a lease agreement for the trucks driven by such drivers, and the lease agreement must show that the compensation for the leased equipment is on a time basis and not based on the amount of work accomplished. The lease agreements must be available for inspection by NDOR personnel.
- (5) Any supplemental truckers employed under this arrangement must still carry the minimum automobile liability coverage specified in the contract. It shall be the duty of the Prime Contractor to ensure that the supplemental truckers have such coverage in effect. Evidence of proper insurance must be presented for verification on demand.

SHOP PLANS AND ELECTRONIC SHOP DRAWINGS (A-43-0514)

Paragraph 5. of Subsection 105.02 in the *Standard Specifications* is amended to provide that the Contractor may furnish shop plans on half-size plan sheets [11x17 inches (297x420mm)], provided all information is legible.

Subsection 105.02 of the Standard Specifications is amended to include the following:

8. a. (1) The Contractor may provide electronic working drawings in a Portable Document Format (PDF). The PDFs shall be sized to print on an 11 x 17 inch sheet of paper and have a minimum resolution of 300 dpi. Each sheet of the shop drawings shall have a space provided for an electronic stamp that measures 2.5 inches x 3.5 inches when printed.
- (2) Electronic working drawing files shall be named with the following file naming format:

Control Number_Brief Description_Date.pdf
For example: 12345_FloorDrains_12May2013.pdf
- (3) The project number, control number, and project location as it appears on the plans shall be shown on each sheet of the shop drawings or on the front sheet only for catalog cuts, design calculations and product data sheets. Structure numbers shall be included, if applicable.
- b. No electronic working drawings shall be submitted to the Engineer unless they have been checked by the Contractor. The electronic submittal shall be accompanied by a Contractor's letter of approval in a PDF format. The letter of approval shall clearly indicate that the Contractor is responsible for any errors on the working drawings.
- c. (1) Electronic submittals shall be submitted by email to the following address:

DOR.ShopDrawings@nebraska.gov
- (2) Attachments shall be limited to 25 MB of data per email. Larger files shall be separated and sent in multiple emails.
- (3) Electronic working drawings will only be accepted from the Prime Contractor.

**LIABILITY INSURANCE
(A-55-0414)**

Subsection 107.13 in the Standard Specifications is void and superseded by the following:

107.13 – Liability Insurance

Prior to execution of the contract, the Contractor shall obtain insurance coverage to fully protect it from loss associated with the work, and have at a minimum the insurance described below:

1. General Liability:
Limits of at least:
 - \$ 1,000,000 per Occurrence
 - \$ 2,000,000 General Aggregate
 - \$ 2,000,000 Completed Operations Aggregate
 - \$ 1,000,000 Personal and Advertising Injury
- a. Contractor shall be responsible for the payment of any deductibles.
- b. Coverage shall be provided by a standard form Commercial General Liability Policy (CG0001 or equivalent) covering bodily injury, property damage including loss of use, and personal injury.
- c. The General Aggregate shall apply on a Per Project Basis.
- d. The State of Nebraska, Department of Roads, shall be named as an Additional Insured on a primary and non-contributory basis including completed operations for three (3) years after final acceptance and payment.
- e. Contractor agrees to waive its rights of recovery against the State of Nebraska, Department of Roads. Waiver of Subrogation in favor of the State of Nebraska, Department of Roads shall be added to the policy.
- f. Contractual liability coverage shall be on a broad form basis and shall not be amended by any limiting endorsements.
- g. If work is being performed near a railroad track, the 50' railroad right-of-way exclusion must be deleted.
- h. Products and completed operations coverage in the amount provided above shall be maintained for the duration of the work, and shall be further maintained for a minimum period of three years after final acceptance and payment.
- i. Coverage shall be included for demolition of any building or structure, collapse, explosion, blasting, excavation and damage to property below surface of ground (XCU coverage).

- j. Policy shall not contain a total or absolute pollution exclusion. Coverage shall be provided for pollution exposures arising from products and completed operations as per standard CG0001 Pollution Exclusion or equivalent. If the standard pollution exclusion as provided by CG0001 has been amended, coverage must be substituted with a separate Pollution Liability policy of \$1.0 million per occurrence and \$2.0 million aggregate. If coverage is provided by a "claims made" form, coverage will be maintained for three years after project completion. Any applicable deductible is the responsibility of the Contractor.
2. Automobile Liability:
Limits of at least:
\$ 1,000,000 CSL per Accident
- a. Coverage shall apply to all Owned, Hired, and Non-Owned Autos.
 - b. If work is being performed near a railroad track, the 50-foot railroad right-of-way exclusion must be deleted.
 - c. Contractor agrees to waive its rights of recovery against the State of Nebraska, Department of Roads. Waiver of Subrogation in favor of the State of Nebraska, Department of Roads, shall be added to the policy.
 - d. Automobile liability coverage shall be obtained from an insurance carrier who is licensed with the Nebraska Department of Insurance.
3. Workers' Compensation:
Limit: Statutory coverage for the State where the project is located.
Employer's Liability limits: \$500,000 Each Accident
\$500,000 Disease – Per Person
\$500,000 Disease – Policy Limit
- a. Contractor agrees to waive its rights of recovery against the State of Nebraska, Department of Roads. Waiver of Subrogation in favor of the State of Nebraska, Department of Roads shall be added to the policy.
 - b. Workers' compensation coverage shall be obtained from an insurance carrier who is licensed with the Nebraska Department of Insurance.
 - c. Where applicable, the Longshore and Harborworkers Compensation Act endorsement shall be attached to the policy.
4. Umbrella/Excess:
Limits of at least:
\$1,000,000 per Occurrence
- a. Policy shall provide liability coverage in excess of the specified Employers Liability, Commercial General Liability and Automobile Liability.
 - b. The State of Nebraska, Department of Roads, shall be an "Additional Insured."
 - c. Contractor agrees to waive its rights of recovery against the State of Nebraska, Department of Roads. Waiver of subrogation in favor of the State of Nebraska, Department of Roads shall be provided.

5. Pollution Liability:
 - a. When “hazardous wastes” or contaminated or polluted materials must be handled and/or moved, the Contractor shall obtain Pollution Liability Coverage with minimum limits of \$1,000,000 per occurrence and \$2,000,000 aggregate.
 - b. If, during the course of construction, hazardous wastes, contaminated or polluted material are discovered on the project, the Contractor shall immediately cease any operation that may disturb these materials, and shall immediately notify the Engineer of all facts related to the discovery of these materials.
 - c. Unforeseen work related to the discovery of hazardous, contaminated or polluted materials on the project, and the extra cost, if any, of pollution liability coverage will be handled as “extra work.”
6. Additional Requirements:
 - a. The Contractor shall provide and carry any additional insurance required by the Special Provisions.
 - b. Except as otherwise provided herein, all insurance shall be kept in full force and effect until after the State releases the Contractor from all obligations under the contract.
 - c.
 - (1) If any of the work is sublet, equivalent insurance shall be provided by or on behalf of the subcontractor or subcontractors (at any tier) to cover all operations.
 - (2) Approved trucking subcontractors (at any tier) who are being utilized only for the purpose of hauling materials shall be exempt from the requirements of Paragraphs 1, 4, and 5.
 - (3)
 - (i) When a Contractor or subcontractor chooses to employ a trucker by carrying the driver on his or her payroll and entering into a lease agreement for the truck, the owner-operator of the truck shall be required to comply with the Automobile Liability provisions of Paragraph 2.
 - (ii) Furthermore, it shall be the duty of the Prime Contractor to ensure that the owner-operator of the truck has such insurance in effect. The Prime Contractor shall maintain evidence that any truckers so utilized (at any tier) are insured to the minimum limits specified and be able to furnish documentation of the same on demand.
 - (iii) Failure to ensure that insurance coverage exists and failure to maintain evidence thereof shall be considered a breach of the contract.
 - d. Any insurance policy shall be written by an insurance company with a Best’s Insurance Guide Rating of A – VII or better.
 - e. Prior to execution of the contract, Contractor shall provide the State of Nebraska, Department of Roads evidence of such insurance coverage in effect in the form of an Accord (or equivalent) certificate of insurance executed by a licensed representative of the participating insurer(s).

Certificates of insurance shall show the Nebraska Department of Roads as the certificate holders.

- f. For so long as insurance coverage is required under this agreement, the Contractor shall have a duty to notify the Department when the Contractor knows, or has reason to believe, that any insurance coverage required under this agreement will lapse, or may be cancelled or terminated. The Contractor must forward any pertinent notice of cancellation or termination to the Department at the address listed below by mail (return receipt requested), hand-delivery, or facsimile transmission within 2 business days of receipt by Contractor of any such notice from an insurance carrier. Notice shall be sent to:

Nebraska Department of Roads
Construction Division --- Insurance Section
1500 Highway 2, P.O. Box 94759
Lincoln, NE 68509-4759

Facsimile No. 402-479-4854

- g. Failure of the owner or any other party to review, approve, and/or reject a certificate of insurance in whole or in part does not waive the requirements of this agreement.
- h. The limits of coverage set forth in this document are suggested minimum limits of coverage. The suggested limits of coverage shall not be construed to be a limitation of the liability on the part of the Contractor or any of its subcontractors/tier subcontractors. The carrying of insurance described shall in no way be interpreted as relieving the Contractor, subcontractor, or tier subcontractors of any responsibility or liability under the contract.
- i. If there is a discrepancy of coverage between this document and any other insurance specification for this project, the greater limit or coverage requirement shall prevail.

CONSTRUCTION DETAILS

FUEL COST ADJUSTMENT PAYMENT (B-1-0708)

Paragraph 16.a. of Subsection 205.05 in the Standard Specifications is amended to provide that the references to fuel cost fluctuation will be 5% instead of the 10% shown.

The fuel use factor, "F", shown in Paragraph 16.c. of Subsection 205.05 is void and superseded by the following:

F = English

The fuel use factor for diesel fuel, in gallons per cubic yard. For the items of work "Excavation", "Excavation, Borrow", and "Excavation, Established Quantity", "F" shall be equal to 0.20. For the item of work "Earthwork Measured in Embankment", "F" shall be equal to 0.27.

Metric

The fuel use factor for diesel fuel, in liters per cubic meter. For the items of work "Excavation", "Excavation, Borrow", and "Excavation, Established Quantity", "F" shall be equal to 0.99. For the item of work "Earthwork Measured in Embankment", "F" shall be equal to 1.32.

Paragraph 16.d. of Subsection 205.05 is void and superseded by the following:

- d. The allowable price differential, "D", for the current estimate will be computed according to the following formula:

When the current price, P, is greater than the base price, P(b).

$D = P - 1.05P(b)$, but not less than zero.

When the current price, P, is less than the base price, P(b).

$D = P - 0.95P(b)$, but not greater than zero.

**WATER
(B-1-0307)**

Paragraph 4.a. of Subsection 205.04 in the Standard Specifications is amended to include the following:

Payment shall be made at the established contract unit price.

**EXCAVATION AND EMBANKMENT
(B-1-0212)**

Paragraph 6. of Subsection 205.02 in the Standard Specifications is void and superseded by the following:

6. Frozen Layers:
- a. Thin Frozen Layer. A thin soil layer that freezes during the construction of an embankment may remain provided that the layer:
- (i) had proper density and moisture prior to freezing,
 - (ii) can be readily broke up by a single pass of a tamping (sheepsfoot) roller or track mounted excavator,
 - (iii) is thoroughly scarified into pieces having a single dimension of 3 inches or less, and a second dimension of ½ inch or less, and
 - (iv) is not within 10 inches (measured vertically) of any thin frozen layer that was previously scarified and left in place.

- b. Thick Frozen Layer. A soil layer that freezes during the construction of an embankment, but does not meet the Thin Frozen Layer requirements:
 - (i) may remain in the embankment provided that the layer is thawed and has proper density and moisture after thawing, or
 - (ii) shall be completely removed from the embankment prior to placing any additional embankment material.

**EARTH SHOULDER CONSTRUCTION
(C-5-0311)**

Paragraph 4.b. of Subsection 304.03 of the Standard Specifications is amended to include Paragraph 4.b.(3).

- (3) When asphaltic concrete and earth shoulders are being placed on a multilane, divided highway, the provisions of Paragraphs 4.b.(1) and 4.b.(2) of this Subsection shall be applied to each roadway separately.

Table 304.01 in Subsection 304.03 of the Standard Specifications is void and superseded by the following:

Table 304.01

Timed Allowed to Complete Shoulders	
Length of Pavement Mile (Kilometers) [Entire Project]	Maximum Working Days Allowed To Complete Shoulder
0 to 3.0 (0 to 4.8)	5
More than 3.0 to 4.0 (4.8 to 6.4)	6
More than 4.0 to 5.0 (6.4 to 8.0)	7
More than 5.0 to 6.0 (8.0 to 9.7)	8
More than 6.0 to 7.0 (9.7 to 11.3)	9
More than 7.0 (11.3)	10*

* 10 plus 1 day for every whole 2 miles of project length in excess of 7 miles.

RELOCATE INERTIAL BARRIER SYSTEM

Paragraph 19.b. of Subsection 422.04 in the Standard Specifications is void and superseded by the following:

- b. Relocate Inertial Barrier System” is the pay item for moving the inertial barrier system to a new location after initial installation and operation.

Paragraph 1. of Subsection 422.05 is amended to include the following:

1.	Pay Item	Pay Unit
	Relocate Inertial Barrier System	Each (ea)

**TYPE B HIGH INTENSITY WARNING LIGHTS
(D-6-0307)**

All references in the plans to Type B High Intensity Warning Lights shall be considered void. The plans will not be revised to reflect this change.

**TEMPORARY TRAFFIC CONTROL DEVICES
(Type II Barricades, Reflectorized Drums, 42" (1070 mm) Reflective Cones, and
Vertical Panels)
(D-6-1112)**

Paragraph 2.d. of Subsection 422.03 in the Standard Specifications is void and superseded by the following:

- d. (1) Reflectorized drums used for traffic warning or channelization shall be constructed of lightweight, flexible, and deformable materials, be a minimum of 36 inches (900 mm) in height, and have a minimum width of 18 inches (450 mm), regardless of orientation. The predominant color of the drum shall be orange.
- (2) Steel drums shall not be used.
- (3) The markings on drums shall be horizontal, shall be circumferential, and shall display four 6-inch (150 mm) wide bands of retroreflective sheeting, alternating fluorescent orange - white – fluorescent orange - white. The fluorescent orange sheeting shall meet the luminance requirements of the following table.

FHWA Luminance Factor

Sheeting Type	Luminance Factor Y_T		
	Min	Max	Fluorescence Luminance Factor Limit, Y_F
Fluorescent Orange	25	None	15

- e. When approved by the Engineer or shown in the plans, 42" (1070 mm) reflective cones may be used in lieu of Type II Barricades or Reflectorized Drums. 42" (1070 mm) reflective cones shall include a 30-pound (14 kg) rubber base and display four 6-inch (150 mm) wide bands of retroreflective sheeting, alternating fluorescent orange - white - fluorescent orange - white. 42" (1070 mm) reflective cones shall not be used for lane-closure tapers or shifts.
- f. Rubber base-mounted 36-inch vertical panels shall not be used for channelization when the speed limit exceeds 40 miles per hour.

Paragraph 2.b. of Subsection 422.04 of the Standard Specifications is void and superseded by the following:

- b. (i) Type II Barricades, Reflectorized Drums, and 42" (1070 mm) Reflective Cones shall be counted as "Barricades, Type II" and measured for payment by the number of calendar days each is in place and positioned as shown in the plans or as directed by the Engineer.
- (ii) Vertical Panels shall be measured for payment as permanent "Sign Days" (by the each) by the number of calendar days each vertical panel unit is in place and positioned as shown in the plans or as directed by the Engineer.

Paragraph 2.c. of Subsection 422.04 of the Standard Specifications is amended to include Reflectorized Drums.

Paragraphs 3. and 4. of Subsection 422.05 of the Standard Specifications are void and superseded by the following:

- 3. a. The pay item "Barricade, Type II" is used to pay for three items ("Barricades, Type II", "42" (1070 mm) Reflectorized Cones", and "Reflectorized Drums").
- b. "Barricades, Type II", which includes "42" (1070 mm) Reflectorized Cones", and "Reflectorized Drums", is paid for as an "established" contract unit price item. The established unit price is identified on the "Schedule of Items" shown in the Proposal.
- 4. Payment for vertical panels includes all posts, brackets, or hardware necessary to install and maintain the vertical panel units.

WORK ZONE TRAFFIC CONTROL SIGNS (D-6-1212)

The Department has adopted the FHWA 2009 Manual of Uniform Traffic Control (MUTCD) and the 2011 Nebraska Supplement to the MUTCD as the official guidance for work zone traffic control signs. Many work zone traffic control signs have been revised, redesigned, or replaced in the 2009 MUTCD (and 2011 Nebraska Supplement). Accordingly, all work zone signs shall comply with the following:

- 1 - All signs, regardless of age, shall meet the design standards of the 2009 MUTCD (and 2011 Nebraska Supplement).

**TEMPORARY PAVEMENT MARKING
(D-10-0811)**

Paragraph 4.f. of Subsection 422.01 in the Standard Specifications is void.

Paragraph 6.a.(2) of Subsection 422.03 is void and superseded by the following:

- (2) When the markings are no longer needed, the Contractor shall remove them. If removing markings from the final wearing surface, the removal process shall not mar or damage the surface. Removed markings shall no longer be visible on the final wearing surface.

Paragraph 6. of Subsection 422.03 in the Standard Specifications is amended to include the following:

This work shall consist of installing and removing reflectorized temporary pavement lines of the color, width and line configuration shown in the plans or as designated by the Engineer.

Temporary paint markings will be used on this project. The use of Type I tape will not be permitted and Type II tape may be used for short durations only, as directed by the Engineer. Temporary paint stripes shall be a minimum 4" (100 mm) wide, 10' (3 m) long with a 30-foot (9 m) gap or a minimum 4" (100 mm) wide solid line as shown on the plans.

Temporary pavement marking which is no longer applicable shall be removed as directed by the Engineer.

Paragraph 12.a. of Subsection 422.04 is void and superseded by the following:

- a. "Pavement Marking Removal" and "Temporary Pavement Marking Removal" shall be measured by the linear foot (meter) along the centerline of the traveled roadway for each line removed.

Subsection 422.04 is amended to include the following:

21. The use of paint for Temporary Pavement Marking shall be measured per linear foot (meter) for the item "Temporary Pavement Marking, Type Paint".
22. Temporary pavement marking tape Type II shall be measured per linear foot (meter) for the item "Temporary Pavement Marking, Type II".
23. Initial surface preparation requiring sand or shot blasting shall be measured per linear foot (meter) for the item "Temporary Pavement Marking, Surface Preparation". Surface preparation for repainting, consisting of air blasting and brushing, shall be subsidiary to other items for which payment is made.

Paragraph 1. of Subsection 422.05 is amended to include the following:

Pay Item	Pay Unit
Temporary Pavement Marking Removal	Linear Foot (LF)
Temporary Pavement Marking, Type Paint	Linear Foot (LF)
Temporary Pavement Marking, Type II	Linear Foot (LF)
Temporary Pavement Marking, Surface Preparation	Linear Foot (LF)

Paragraph 9.c. of Subsection 422.05 is void.

Paragraph 13. of Subsection 422.05 is void and superseded by the following:

13. Removal of temporary pavement markings including overlay broken/solid lines will be paid for except:
 - a. When the temporary markings are intended to be covered up by permanent markings.
 - b. When surface preparation removes the temporary markings.

Section 1069 in the Standard Specifications is amended to include the following:

1. Prior to the initial placement of the markings, temporary paint, or Type II tape the pavement upon which the markings are to be placed shall be dry, cleaned and properly prepared by sand or shot blasting, as a minimum, and to the extent recommended by the manufacturer so that all contaminants, loose debris, and other foreign material are completely removed. Surface preparation for any subsequent application shall consist of air blasting and brushing the roadway surface to remove all loose dirt, mud or other debris and to dry the surface. Each additional application of paint shall be applied over the previously painted stripes.

Prior to placing the temporary pavement markings on the prepared surface, the Contractor shall layout, spot or string line the proposed temporary marking location. The temporary markings shall be aligned in such a way as to provide a smooth and gradual transition to and from the existing markings, and throughout both straight and horizontally curved sections of the project.

2. The material used for temporary paint marking shall be a commercially available acrylic resin Type II traffic paint that dries to no pickup in 4 minutes and shall be applied with a minimum of 6 pounds (0.7 kg) of glass beads per gallon (liter). The paint shall be applied at a minimum width of 4 inches (100 mm) and a wet thickness of approximately 15 mils (380 μ m) {approximately 16.5 gallons (39 liters) of paint per mile (kilometer) of solid line}. The equipment used to paint the line shall be a machine designed for the purpose of applying long line traffic lane markings of the type, width and thickness required, and shall be self-propelled or truck mounted and be equipped with an adjustable guide-on to assure proper placement of the line. Hand application, walk behind equipment or towing of the equipment will not be allowed.

Temporary paint lines shall be used on new or existing concrete pavement and asphaltic concrete pavement.

Any temporary painted line or segment of line, placed before December 1, which fails to adhere to the roadway surface for a minimum of 60 days under normal vehicular traffic or which appears wavy, nonuniform, thin, poorly applied, misaligned, beadless or nonreflective, shall be replaced as directed by the Engineer. For temporary painted pavement markings placed between December 1 and March 15, the minimum time requirement shall be 15 days with the same conditions applicable. No direct payment will be made for replacement within the 60 day or 15 day warranty periods.

After the minimum 60 day or 15 day warranty periods, the Contractor may be required to repaint the temporary traffic markings, as directed by the Engineer. Direct payment will be made for each additional application. However, should the additional application fail within the 60 day or 15 day warranty periods, the provisions as stated in the previous paragraph shall apply.

The Contractor must begin each additional repainting application within 72 hours after notification by the Engineer. Should the Contractor fail to begin repainting within this 72 hour period, the Engineer may use State forces or hire a private contractor to repaint the temporary traffic markings. The Contractor will be assessed any costs above the contract unit price "Temporary Pavement Marking, Type Paint" incurred by the State as a result of performing the corrective action by others, and the project will be shut down until the painting is completed.

When painting is required with air temperatures between 38° F (3° C) and 50° F (10° C), the paint shall be heated according to the manufacturer's recommendation prior to application on the dry, clean and properly prepared pavement. Any paint application made when the air temperature is below 38° F (3° C) will be paid for by the State, even if the application falls within either the 60 day or 15 day warranty periods previously described.

3. Temporary pavement marking tape Type II shall be a mixture of high quality polymeric materials and pigments, with glass beads throughout the pigmented portion of the film, and a reflective layer of high index of refraction glass beads bonded to the top surface. The film shall be precoated with a pressure-sensitive adhesive. Unless otherwise specified, the temporary pavement marking shall be 4 inches (100 mm) wide and the reflectorizing glass beads shall be incorporated to facilitate removal of the tape easily from asphalt and Portland cement concrete surfaces intact or in large pieces, at temperatures above 40° F (4° C), either manually or with a recommended roll up device. Removal shall be accomplished without the use of heat, solvents, grinding or sandblasting.

TEMPORARY TRAFFIC CONTROL FOR PERMANENT PAVEMENT MARKING (D-13-1007)

Paragraph 4. of Subsection 423.04 in the Standard Specifications is void.

**INERTIAL BARRIER SYSTEM
(D-14-0509)**

Paragraph 9.b.(5) of Subsection 422.03 in the Standard Specifications is void and superseded by the following:

- (5) All inertial barriers shall have 5 to 15 percent (by volume) rock salt mixed with the filler material.

**WET REFLECTIVE POLYUREA PAVEMENT MARKING, GROOVED
(D-17-1114)**

I. Description

This work shall consist of furnishing and installing wet night retroreflective polyurea pavement markings in accordance with this provision and in conformance to the dimensions and lines shown on the plans or established by the Engineer.

The wet reflective polyurea marking material shall be applied by spray method onto asphaltic cement concrete and Portland cement concrete surfaces. Following an application of glass beads or black aggregate, and upon curing, the resulting marking shall be an adherent reflectorized stripe of the specified thickness and width that is capable of resisting deformation by traffic.

The Contractor shall field verify the pavement marking quantities required for the project prior to purchasing materials. The Department will not be held responsible for the Contractor's shortage or surplus of material. The Contractor's verification of quantities and purchasing material shall not delay the project or the installation of pavement marking when required.

The polyurea pavement marking shall be applied in grooves cut into the surfacing. The grooves shall be made in a single pass dry cut; the equipment used shall be self-vacuuuming and leave the cut groove ready for polyurea pavement marking application. The equipment and method used shall be approved by the polyurea pavement marking manufacturer. The polyurea pavement marking shall be applied in the grooves the same day as the cut. Grooves shall be clean and dry prior to polyurea pavement marking application. All conflicting pavement markings which remain after application of the polyurea pavement markings shall be removed. The removal of conflicting, pre-existing temporary or permanent pavement marking shall be paid for with the appropriate removal pay item. The removal of conflicting temporary or permanent pavement marking placed as part of this work shall be at no cost to the Department.

Groove width: pavement marking width + 1 inch to 2 inch maximum
Groove depth: per manufacturer's recommendations to a minimum of 60 mils
Groove length: full length of marking + required grooving transition
Groove position: 2 inches off of joint line (per plan)

Grooving of the surfacing shall be performed in accordance with the polyurea manufacturer's recommendations. Grooving the surfacing shall not be measured and

paid for but shall be considered subsidiary to "____ Polyurea Pavement Marking, Grooved".

II. Materials

A. Polyurea

Composition Requirements:

Composition requirements are per manufacturer's specifications. The Polyurea Pavement Markings approved for use are shown on the NDR Approved Products List. Markings which have not been previously approved by the Department will not be permitted on the project until approved by the Traffic Engineer.

Properties:

1. **Color and Weathering Resistance:** The mixed polyurea compound, white, yellow and black, when applied to a 3" x 6" aluminum panels at 15±1 mil in thickness with no glass beads or elements and exposed for 500 hours in a Q.U.V. Environmental Testing Chamber, as described in ASTM-G154, Cycle #1, shall conform to the following minimum requirements. The color of the white polyurea system shall not be darker than Federal Standard No. 595A-17778. The color of the yellow polyurea system shall conform to Federal Standard No. 595A-13538. The color of the black polyurea system shall conform to Federal Standard No. 595A-17038.
2. **Track-Free Time (Laboratory):** When tested in accordance with ASTM D 711, the polyurea marking material shall reach a track-free condition in 10 minutes or less for a 15 mil thickness. This test shall be performed with AASHTO Type 1 beads coated at a rate of 0.099 pounds per square foot. The track-free time shall not increase substantially with decreasing temperature.
3. **Adhesion to Concrete:** The polyurea coating, when tested according to ACI Method 503, shall have such a high degree of adhesion to the specified concrete surface that there shall be a 100% concrete failure in the performance of this test. The prepared specimens shall be conditioned at room temperature (75°± 2° F) for a minimum of 24 hours and maximum of 72 hours prior to the performance of the tests indicated.
4. **Adhesion to Asphalt:** The polyurea coating, when tested according to ACI Method 503, shall have such a high degree of adhesion to the specified asphalt surface that there shall be a 100% asphalt failure in the performance of this test. The prepared specimens shall be conditioned at room temperature (75°± 2° F) for a minimum of 24 hours and maximum of 72 hours prior to the performance of the tests indicated.

B. Reflective Media

The reflective media application shall incorporate a double drop technique to maximize wet night reflectivity and color. The reflective media used shall ensure the wet reflective polyurea pavement markings meet the retroreflectance performance requirements in Section II.D.3. The glass beads for drop-on application shall conform to the following requirements *or be an approved equivalent*.

1. Glass Beads

The required glass beads shall be a 60/40 blend (60% sinkers and 40% floaters) of AASHTO M 247-81 Type I gradation 1.5 index glass beads. The glass beads shall have a minimum of 70% Rounds as measured according to ASTM D1155. Crush Resistance shall be measured according to the procedures of ASTM D1213 and shall be a minimum of 30 pounds retained on US #40 Mesh.

Acid Resistance: A sample of glass beads supplied by the manufacturer shall show resistance to corrosion of their surface after exposure to a 1% solution (by weight) of sulfuric acid. The 1% acid solution shall be made by adding 5.7 cc of concentrated acid into 1000 cc of distilled water. CAUTION: Always add the concentrated acid into the water, not the reverse. The test shall be performed as follows:

Take a 1" x 2" sample, adhere it to the bottom of a glass tray and place just enough acid solution to completely immerse the sample. Cover the tray with a piece of glass to prevent evaporation and allow the sample to be exposed for 24 hours under these conditions. Then decant the acid solution (do not rinse, touch, or otherwise disturb the bead surfaces) and dry the sample while adhered to the glass tray in a 150° F (66° C) oven for approximately 15 minutes. Microscopic examination (20X) shall show not more than 15% of the beads having a formation of very distinct opaque white (corroded) layer on their entire surface.

2. Wet Reflective Media

Wet reflective media shall be approved for use by the polyurea manufacturer. The Wet Reflective Media approved for use are shown in the NDR Approved Products List.

C. Non-reflective Media

Black aggregate shall be broadcast to saturation on all black lines to provide a matte, non-reflective finish. The black aggregate shall be either a fine or medium gradation.

D. Finished Markings

Because of normal variances in road surfaces, application processes and measurement, the properties of markings made from the materials specified herein will vary from one installation to the next. When the materials are applied according to the specifications in Section III, they shall be capable of forming markings with the following reproducibility of properties:

1. On-the-road Track-Free Time: When installed at 77° F and at a wet film thickness of 15±1 mils, the markings shall reach a no-track condition in less than 10 minutes. Track-free shall be considered as the condition where no visual deposition of the polyurea marking to the pavement surface is observed when viewed from a distance of 50 feet, after a free-rolling traveling vehicle's tires have passed over the line. The track-free time shall not increase substantially with decreasing temperature.
2. Skid Resistance: The average initial skid resistance shall be 45 BPN or greater when tested according to ASTM E303.
3. Retroreflectance – Required initial retroreflectance values are shown in the table below. Typical retroreflectivity is determined as the average of many readings (mcd(ft-2)(fc-1)) metric equivalent (mcd(m-2)(lux-1)) as described below.

Average Minimum Initial Retroreflectance		
	White	Yellow
Dry (ASTM E1710)	500	350
Wet Recovery (ASTM E2177)	350	275
Wet Continuous (ASTM E2832)	100	75

- 3.1.1 Some reasonable variance should be expected (for example, application on very rough road surfaces or differences in glass beads).
- 3.1.2 The initial retroreflectance value of a single installation or unit of work shall be the average value determined according to the measurement and sampling procedures outlined in ASTM D7585, using a 30-meter (98.4 feet) retroreflectometer, except as modified below. The 30-meter retroreflectometer shall measure the coefficient of retroreflected luminance, R_L at an observation angle of 1.05 degrees and an entrance angle of 88.76 degrees. R_L shall be expressed in units of millicandelas per square foot per foot-candle [mcd(ft²)(fc⁻¹)]. The metric equivalent shall be expressed in units of millicandelas per square meter per lux [mcd(m²)(lux⁻¹)].
- 3.1.3 The initial retroreflectance values of the pavement marking shall be measured no sooner than 48 hours after application, but not later than 30 days after application. The Contractor shall provide an acceptable 30-meter retroreflectometer to use on the project (the retroreflectometer will remain the property of the Contractor). The contractor will take measurements in the presence of the Engineer. Prior to taking measurements, the Contractor shall

calibrate the retroreflectometer according to the manufacturer's requirements.

Measurements will be taken at equally spaced (or nearly so) test areas located by the Engineer in each evaluation section. An evaluation section is defined as a 3 mile (or major fraction) portion of a segment. If the last evaluation section is less than 1.5 miles in length, it shall be combined with the preceding section.

The test areas shall be at least 400 ft. in length and a minimum of 10 readings shall be taken over the length of each test area.

All measurements shall be made in the direction of travel. On centerlines of undivided highways, measurements shall be taken in both directions in each test area and averaged to determine the value of that color line in that test area.

Measurements shall be taken for each type and color of line in the evaluation section.

Individual symbols and legends will be treated as separate evaluation sections. Three (3) readings shall be taken on each symbol to determine the average retroreflectance value for the symbol.

The Department will do verification testing. When the average of the readings for an evaluation section fall below the minimum, the entire section represented by those readings will be further evaluated by the Engineer and may be subject to removal and replacement.

- 3.1.4 The Department may elect to determine wet retroreflectance values measured under a "condition of continuous wetting" (simulated rain) in accordance with ASTM E2832. To reduce variability between measurements, the test method shall be performed in a controlled laboratory environment while the marking is positioned with a 3 to 5 degree lateral slope. Measurements shall be reported as the average of the minimum of three locations. Samples of the completed finished product shall be applied to flat panels during application and brought back to the lab for testing. When such samples are taken, the Department will furnish the panels.

III. Application

The Contractor shall furnish equipment and apply the materials according to the following specifications:

A. Equipment

Application equipment shall be capable of producing markings that meet the specifications of the manufacturer's listed on the NDR Approved Products List for Polyurea Pavement Marking.

At any time throughout the duration of the project, the Contractor shall provide free access to his application equipment for inspection by the Engineer, his authorized representative or a materials representative.

When black and white polyurea are applied together to create a contrast pattern, they shall be applied from one truck in a single pass operation.

B. Application Conditions:

1. **Moisture:** The markings shall only be applied during conditions of dry weather and when the pavement surface is dry and free of moisture.
2. **Air Temperature:** The markings shall only be applied when road and air temperatures are above 40 degrees F, unless manufacturer's guidelines state otherwise.
3. **Surface Preparation:** Marking operations shall not begin until applicable surface preparation work is completed and approved by the Engineer.
 - 3.1 Prior to applying the markings, the Contractor shall remove any remaining existing markings to expose a minimum of 80% of the pavement surface.
 - 3.2 Prior to applying the markings, the Contractor shall remove all curing compounds on new Portland cement concrete surfaces.
 - 3.3 Prior to applying the markings, the Contractor shall remove all dirt, sand, dust, oil, grease and any other contaminants from the road surface.
 - 3.4 Application over temporary paint is not acceptable.
4. **Dimensions:** The pavement markings shall be placed only on properly prepared surfaces and at the widths and patterns as designated in the contract. The markings shall be applied in accordance with the "Manual on Uniform Traffic Control Devices" and in accordance with the Engineer's plans.

Any markings that are found to be 0.5 inches less than the width shown in the plans shall be removed and replaced by the Contractor.

5. **Other Restrictions:** The Engineer and/or Contractor shall determine further restrictions and requirements of weather and pavement conditions necessary to meet the all other application specifications and produce markings that perform to the satisfaction of the Engineer.
6. **Binder Thickness:** The polyurea binder (mixed Part A and Part B) coating shall be applied at rates to achieve minimum uniform wet thicknesses as follows:

Surface Type	Recommended Polyurea Pavement Marking Thickness (1 inch=1000 mils)
Existing Smooth Asphalt or Concrete Surface	20±2 mils
New Concrete Surface ¹	20±2 mils
New Asphalt Surface (Standard Asphalt Mix)	20±2 mils
Open Grade Friction Course (OGFC) or Stone Matrix Asphalt (SMA) ²	25±2 mils
Rough Concrete or Asphalt	22±2 mils
Concrete or Asphalt after Grinding Off Pavement Markings ³	22±2 mils

- ¹ Use thicker binder (20 mils) on new concrete surfaces with heavy tines.
- ² Very large aggregate sizes for open grade friction course or stone matrix asphalt mixes may require a thickness of 25 mils for proper coverage.
- ³ Pavement marking thickness determined by the type of surface and roughness/texture created from grinding operation.

7. **Reflective Media Application:** The Contractor shall ensure that the reflective media are properly set in the polyurea coating so that their exposed portions are free of polyurea coating material. The specified reflective media shall be dropped per the manufacturer's specified rates to achieve their recommended coating weights:
8. **Volumetric Proportioning:** The Contractor shall ensure proper proportioning as required by manufacturer's specifications and mixing of the polyurea components so that the markings are adequately hardened throughout and are free of soft or uncured material. Typically, such areas will darken over time from dirt and tire residue.

9. **Overspray:** The Contractor shall ensure the polyurea coating does not exhibit excessive overspray.
10. **Adhesion:** The Contractor shall ensure that the polyurea coating is well adhered to the road surface, and that the reflective media are well adhered to the binder.

IV. **Observation Period**

Following initial completion of all pavement marking, there will be a 180-day observation period before final acceptance. During the observation period, the Contractor, at no expense to the Department of Roads, shall replace any marking that the Engineer determines are not performing satisfactorily due to defective materials and/or workmanship in manufacture and/or application. At the end of the observation period the minimum required retention percentage for marking installed shall be 90%.

Determination of Percentage Retained - The percentage retained shall be calculated as the nominal area of the strip less the area of loss divided by the nominal area and expressed as a percentage of the nominal area. A claim, made by the State against the Contractor, shall be submitted to the Contractor in writing within 30 days after the 180-day observation period. When such a claim is made prior to August 1, the replacement material shall be installed during that same construction season. Replacement material for any claim after August 1, shall be installed prior to June 1, of the following year. Marking replacement shall be performed in accordance with requirement specified herein for the initial application, including but not limited to surface cleaning, sealer application, etc.

Final acceptance of all marking will include an inspection of the appearance of the markings during daylight and darkness. Any markings that fail to have a satisfactory appearance during either period, as determined by the Engineer, shall be reapplied at no expense to the Department of Roads.

Final acceptance of the pavement marking will be: (1) 180 days after the initial completion of all work, or (2) upon completion of all corrective work, whichever occurs last.

V. **Contract Units and Basis for Payment**

- A. Linear pavement markings will be measured in linear feet complete-in-place for the width specified.
- B. Arrows and Legends are measured by the each.

Subsection 423.05 of the Standard Specifications is amended to include the item: " Polyurea Pavement Marking, Grooved". Payment shall be full compensation for grooving the pavement surface, furnishing and applying all markings, and for all materials, labor, tools, equipment and incidentals necessary to complete the work.

Payment will be made under:

Pay Item	Pay Unit
____ Polyurea Pavement Marking, Grooved	Linear Feet
____ Polyurea Pavement Marking, Grooved	Each

Payment is full compensation for all work prescribed in this Section.

CONCRETE PROTECTION BARRIERS (D-20-0614)

Guidance for concrete protection barriers:

1. Type A: 4-loop barriers with a large opening at the bottom.
 Type B: 6-loop barriers with 4 lifting slots and no slots for tie-down rods.
 Type C: 6-loop barriers with 4 lifting slots and 6 slots for tie-down rods.
2. Barriers Type A, B and C may be used on this project and may directly be pinned to each other in the same installation arrangement; however, only Type B or C concrete protection barriers shall be allowed for use on any Interstate roadway or Interstate bridge.
3. Other existing barriers meeting NCHRP 350 or MASH testing guidelines and FHWA approval may only be used with written permission (containing this project name and/or control number) from the District and Roadway Design Division.
4. If new barriers are to be fabricated for use on this project, only Type C barriers shall be fabricated.

Paragraph 5 of Subsection 422.03 in the Standard Specifications is amended to include the following:

- f. (1) Concrete protection barriers that become dislodged or moved out of alignment shall be placed back in alignment as soon as practical. If the dislodged barriers are considered to be a hazard to the traveling public by the Engineer, or the barriers encroach into the traveled lane, the barriers shall be realigned within four (4) hours of the time the Contractor is notified. For each occurrence, failure to realign the barriers within the four (4) hour time period will result in the assessment of a lump sum \$1,000 liquidated damage assessment and the Engineer may proceed to correct the adverse condition(s) in a manner that is deemed appropriate. The Contractor will also be assessed the cost incurred when the action is performed by others. This assessment has not been provided for elsewhere in the contract and shall be considered in addition to other liquidated damage assessments which are a part of the contract.

**SURVEILLANCE OF TEMPORARY TRAFFIC CONTROL DEVICES
(D-18-0614)**

Paragraphs 2.i., 2.j.(2)(ii), and 2.k. of Subsection 422.01 of the Standard Specifications are void and superseded by the following:

The Contractor shall provide continuous Surveillance of Temporary Traffic Control Devices on a 24-hours-per-day basis during construction activities and when lanes or ramps are closed. Surveillance will not be required when all lanes and ramps are open to traffic and equipment and traffic control devices have been removed and placed a safe distance away from the roadway (i.e., during specified holidays, during peak hours, and on UNL home football game days for projects east of Highway US-281).

Surveillance shall be utilized from June 29, 2015, to November 28, 2015, or as otherwise directed by the Engineer.

The Contractor shall designate personnel, other than the Project Superintendent, to provide the continuous 24-hour surveillance. These personnel shall be responsible for monitoring the work zone, identifying deficiencies, and effecting the immediate repair, correction or replacement of the traffic control devices.

Individuals assigned to perform the surveillance of traffic control devices on the project shall be dedicated to the purpose of monitoring and maintaining the traffic control devices.

The personnel assigned shall also be responsible for completing a Traffic Control Inspection form, provided by the Engineer, at the completion of each 24-hour period. These forms shall be submitted daily to the Engineer, either in person or via facsimile transmission.

These individuals shall possess a valid Flagger Certification Card and also be qualified by having attended and having satisfactorily passed the examination which accompanies the training for the course for Traffic Control Technician or Traffic Control Supervisor offered by the American Traffic Safety Services Association (ATSSA) --- the training having been completed no more than 4 years prior to working on the project --- or by certification according to the Department's Certification Program for Assistant Traffic Control Managers --- the training having been completed no more than 2 years prior to working on the project. Documentation of the surveillance personnel's training or certifications shall be provided to the Engineer.

In order to be qualified according to the Department's Certification Program for Assistant Traffic Control Managers, the individual must:

- 1 – View the 47-minute video "Training and Certification of Assistant Traffic Control Managers."
- 2 – Correctly answer 80 percent of the questions on an examination that accompanies the video.

Upon satisfactory completion of the training and examination procedure, the trained individual shall be issued an Assistant Traffic Control Manager Certification Card by the examining Contractor. The individual's name, last four digits of Social Security Number, and test score shall be reported to the Construction Engineer on DR Form 90a, "Certification Report for Assistant Traffic Control Managers."

The video, examination forms, Assistant Traffic Control Manager Cards, and Certification Reports for Assistant Traffic Control Managers shall be furnished by the Department.

"Continuous Surveillance" shall be defined as having one or more persons on the project at all times. It is assumed that these personnel will be assigned in three 8-hour shifts per day, with one 30-minute meal break and two 15-minute breaks per shift. Ultimately, however, shift and break lengths shall be determined by the Contractor.

The Contractor shall provide the Engineer with a means of contacting or locating the 24-hour surveillance personnel on the project and shall also provide the Engineer with the names and telephone numbers of personnel to contact if the 24-hour surveillance personnel cannot be located on the project.

The Department expects deficiencies to be corrected immediately upon detection, but in no case should the time limit for correction exceed sixty minutes. Failure to (1) correct deficiencies or (2) respond to notifications from the Department or law enforcement officials within the sixty-minute time period will result in the assessment of a \$1,000 liquidated damage assessment. This liquidated damage assessment will be assessed per occurrence and per calendar day that the deficiency is not corrected. This assessment will be in addition to other liquidated assessment described elsewhere in the proposal. *[If applicable, Exception: the replacement and repositioning of tubular posts shall be performed within the time period stipulated in paragraph 13.c.(3) of Subsection 422.03. Also, the Contractor shall be responsible for immediate removal of tubular posts that become dislodged and of all other objects that encroach or impede traffic.]*

Additionally, if necessary, the Engineer may proceed to correct deficiencies in a manner that he or she deems appropriate and assess the Contractor for the costs incurred as a result of the performance of the corrective action by others.

Subsection 422.04 of the Standard Specifications are amended to include the following:

This work shall be measured and paid for by the calendar day for the item "Surveillance of Temporary Traffic Control Devices". This price shall be considered full compensation for all labor, materials, equipment, tools and incidentals necessary to complete the work.

Subsection 422.05 of the Standard Specifications is amended to include the following:

Payment for "Surveillance of Temporary Traffic Control Devices" will not be made for any day 24-hour surveillance is not provided and will not extend beyond the last working day or calendar day allowed by the contract, except for any approved extension of contract time allowance.

**RUMBLE STRIPS
(E-13-0911)**

This work consists of cutting rumble strips in pavements to the dimensions, spacing, and at the locations shown in the plans or directed by the Engineer. The cutting head shall have the cutting tips arranged in a pattern as to provide a smooth cut [approximately 1/16" (2 mm) between peaks and valleys].

Alignment of the edge of the pattern will be randomly checked by the Engineer. Any rumble strips misaligned [+/- 2 inches (+/-50 mm)] shall be re-cut.

The Contractor shall demonstrate to the Engineer on an initial 500 foot (150 m) test section that the equipment and method will provide the desired milled rumble strip and surface inside each depression without tearing, snagging, or chipping the pavement. If the desired results are not being provided, as determined by the Engineer, the Contractor shall provide new equipment or method, or make necessary adjustments to provide the desired results. If the initial 500 foot (150 m) section results are unsatisfactory it will be repaired or replaced as determined by the Engineer, at no additional cost to the Department.

Excess waste material resulting from the operation shall be removed on a daily basis by use of a power broom or other method approved by the Engineer. Excess waste material shall be removed prior to opening the adjacent lane to traffic.

Any joint that had been previously sealed and then was damaged due to the installation of the rumble strip shall be resealed as directed by the Engineer.

The Contractor shall not place rumble strips on bridge decks and bridge approach slabs.

Method of Measurement

Each shoulder receiving rumble strips shall be measured separately in stations of 100 feet (100 meters). Centerline rumble strips placed left and right of centerline, as shown in the plans, shall be measured separately in stations of 100 feet (100 meters). Stations shall be measured horizontally along the project centerline between the beginning and ending points. Deductions will be made for all areas where rumble strips are not required.

Basis of Payment

Pay Item	Pay Unit
Rumble Strips, Asphalt _____	Station (Sta) Station (StaM)
Rumble Strips, Concrete _____	Station (Sta) Station (StaM)

Payment is full compensation for all work required to install the rumble strips, and resealing joints as required. No additional payment will be made for the test sections that were deemed unsatisfactory.

PORTLAND CEMENT CONCRETE PAVEMENT SMOOTHNESS (F-23-1112)

Section 602 in the Standard Specifications is void and superseded by the following:

General

1. This specification establishes a standard for Portland cement concrete pavement smoothness, and defines defective pavement smoothness. The intent of the specification is to produce a finished Portland cement concrete pavement driving surface with an International Roughness Index (IRI) no greater than 93 inches per mile.
2. Pavement smoothness will be evaluated as prescribed in this section when the pay item "Portland Cement Concrete Pavement Smoothness" is included in the contract.
3. When the pay item "Portland Cement Concrete Pavement Smoothness" is not included in the contract, the Portland cement concrete pavement shall be evaluated in accordance with Paragraph 9.b. of Subsection 603.03.

Equipment

1. The Contractor shall furnish a non-contact inertial pavement profiler that meets the requirements of ASTM Standard E 950, certified by the manufacturer. The profiler must be approved by the Nebraska Department of Roads as specified in Subsection 602.03.
2. The non-contact profiler may be a lightweight version or a high speed version.
3. The non-contact profiler shall be equipped with a computerized system that will record, analyze, and print the test data. The profiler must also be equipped with a large-footprint height sensor specifically designed for surface profile measurements on textured Portland cement concrete surfaces.
4. The non-contact profiler shall produce a printed pavement profile report. The report shall include the following information.
 - a. Project number
 - b. Test date
 - c. Traffic lane
 - d. Test direction
 - e. Test path
 - f. Pass number (1 for initial test; 2, 3, etc. for repeat tests)
 - g. Operator's name
 - h. Project stations
 - i. Data filter values
 - j. IRI values for each test section

- k. Bump and dip locations for each test section, as determined by California profilograph emulation
- l. California profilograph emulation traces (profilograms) for each test section with correctable bumps or dips

602.03 – Certification and Independent Assurance Testing

1. The Department shall calibrate and certify the Contractor's non-contact profiler annually at a test site established by the Department.
 - a. The non-contact profiler shall be inspected for compliance with general equipment requirements, including data analysis system, guidance system, and overall condition.
 - b. The non-contact profiler shall be calibrated for distance measurement by moving it over the prescribed path of a pre-measured test distance to determine its distance calibration factor.
 - c. The non-contact profiler shall be checked for vertical measurement accuracy by performing the height measurement calibration procedure described in Section 6 of AASHTO Designation PP 49-03, Certification of Inertial Profiling Systems.
 - d. The non-contact profiler shall be checked for overall performance by operating it over the prescribed path of a pre-measured pavement test section at its normal operating speed.
 - e. Distance measurement indicated by the non-contact profiler shall be within 0.2% tolerance of the actual pre-measured test section distance. To ensure accurate distance measurement during test runs, the air pressure of the distance measurement tire must always be maintained at the same level used for calibration.
 - f. The IRI reported by the non-contact profiler for the test section shall be within 10.0% tolerance of the IRI reported by a Nebraska Department of Roads non-contact profiler for the same test section.
 - g. A dated and signed decal will be placed on the non-contact profiler to certify its acceptability for use on Nebraska Department of Roads pavement construction projects. The certification expires one year from its issue date.
2. The Department shall certify the Contractor's non-contact profiler operator at least every 5 years. The operator may be certified by presenting certification from another state highway agency or by completing certification training conducted by the Nebraska Department of Roads.
3. The Department shall schedule and perform Independent Assurance tests for the Contractor's non-contact profilers and operators at least once per construction season. Independent Assurance testing shall be conducted at a randomly

selected time on an active construction project. The criteria for the test will be similar to those used for certification.

602.04 – Profile Test Procedures

1. The Contractor shall perform all pavement smoothness specification tests with a Department certified profiler.
2. The Engineer shall furnish a report form to the Contractor identifying all required test sections.
 - a. The pavement surface shall be divided into lane-width segments that end at a bridge, railroad crossing or other designated termini.
 - b. The lane-width segments shall be further divided into individual 528 feet long test sections, in the direction of project stationing. The last test section in a segment is usually shorter than 528 feet.
 - c. If a test section is less than 300 feet long, it shall be combined with the preceding 528 feet long test section for analysis.
3. The Contractor's certified non-contact profiler operator shall perform smoothness specification tests in the Engineer's presence.
4. Smoothness testing shall be performed during normal daylight working hours unless otherwise approved by the Engineer.
5. The non-contact profiler operator shall perform pavement smoothness measurements in the right-hand or left-hand wheel path of all driving lanes, as directed by the Engineer, including climbing and fly-by lanes. The wheel path is the path followed by the right or left wheels of a truck or car traveling in the center of a traffic lane. It is assumed to be 3 feet from the left or right lane lines. In urban areas, where inlet block-outs or manholes are in the right or left hand wheel path, the pavement smoothness measurements shall be made in a location determined by the Engineer.
6. The Contractor shall remove all objects and foreign material from the pavement surface before testing, including any extra run-in or run-out lengths required for the non-contact profiler. Unless adequate traffic and personnel control is provided by the Contractor, the non-contact profiler must not be operated in active construction zones congested with construction equipment or personnel that could result in collision with the profiler.
7. The non-contact profiler operator shall guide the profiler along the specified wheel path of each traffic lane at a constant speed and directional path throughout the length of pavement being tested. The speed of the non-contact profiler must be within the speed range recommended by the manufacturer. Sudden changes in speed or direction during a test run will disqualify that test, and a new test must be performed.

8. A lateral location indicator shall be used to align the non-contact profiler in the required test path during testing. Pavement edges, longitudinal joints, or longitudinal pavement markings may be used as reference lines.
9. Before testing, the non-contact profiler operator shall perform routine check procedures of the measurement system as recommended by the manufacturer. To ensure consistent distance measurement, the operator shall also check and adjust the distance recording wheel tire pressure several times a day.
10. All station references on the non-contact profiler reports shall be actual project stations. Stations shall be accurately noted on any printed profiles at least every 100 feet. The distance measured by the non-contact profiler shall compare within 0.2 percent of the actual distance tested, as determined using project stationing, for all testing and retesting runs. Test runs that do not compare within 0.2 percent will disqualify that test. New tests must be performed for all disqualified tests, following calibration of the distance measuring system.
11. Immediately after completion of the tests, the non-contact profiler operator and the Engineer shall sign any printed reports and profiles to verify their authenticity. The signed prints then become the property of the Department.
12. The Engineer shall perform or schedule verification tests on at least 10 percent of the lane miles of pavement surface, with a non-contact profiler owned by the Department.
13. If the verification test, Independent Assurance tests, or other observations indicate that the Contractor's procedures or results are not acceptable or accurate, the Engineer may do any of the following.
 - a. Require the Contractor to calibrate the non-contact profiler and re-run the tests.
 - b. Disqualify the Contractor's equipment or operator.
 - c. Perform the tests for part, or all, of the project with a non-contact profiler owned by the Department, and charge the Contractor \$500.00 per lane mile for all testing done by the Department.
14. The following areas of pavement shall be excluded from the IRI requirements, unless otherwise specified in the special provisions.
 - a. Pavement on horizontal curves having a centerline radius of curvature of less than 1,000 feet, and pavement within the superelevation transition of such curves.
 - b. Pavement within 50 feet of a transverse joint that separates the pavement from an approach slab to a bridge deck or existing pavement not constructed under the contract.
 - c. Pavement for truck weigh stations or rest areas, acceleration/deceleration lanes, and interchange ramps and loops.

- d. Pavement within 50 feet of railroad crossings and associated transitions.
 - e. Pavement with a posted speed limit of 45 miles per hour or less.
 - f. Mandated blockouts for access at intersections and driveways including 50 feet on either side.
 - g. Pavement that would require handwork by normal industry practices.
 - h. Additional exceptions shown on the summary sheet in the plans.
15. Excluded pavement sections shall be measured for bumps and dips with either a profilograph, non-contact profiler, or a 10-foot straight edge. If the profilograph or non-contact profiler is used, the bump or dip surface deviation shall not exceed 0.30 inch. The deviation of the surface shall not exceed 1/8 inch, if a 10-foot straightedge is used.

602.05 – Evaluation

- 1. The Contractor shall determine the IRI and number of correctable bumps and dips for each test section, record the information on the report form, and provide a copy of the report, along with the corresponding printed reports and profiles, to the Engineer.
 - a. The International Roughness Index (IRI) shall be calculated by the non-contact profiler software using the quarter-car simulation. IRI shall be reported in units of inches per mile.
 - b. Correctable bumps shall be separately identified by the non-contact profiler software in a summary report using the California profilograph emulation. Bumps will appear as high points on the printed profile, and correspond to high points on the pavement surface. Correctable bumps are vertical deviations on the pavement surface that exceed 0.30 inch in height above a base line span of 25 feet.
 - c. Correctable dips shall be separately identified by the non-contact profiler software in a summary report using the California profilograph emulation. Dips will appear as low points on the printed profile, and correspond to low points on the pavement surface. Correctable dips are vertical deviations on the pavement surface that exceed 0.30 inch in depth below a base line span of 25 feet.

602.06 – Pavement Surface Correction

1. The Contractor shall locate and perform all required pavement surface corrective work, with the approval of and in the presence of, the Engineer. Corrective work may also be required for any combination of bumps, dips, or other roughness that, in the opinion of the Engineer, produces an objectionable ride. The Contractor may also locate and perform voluntary corrective work as described in Paragraphs 2.b and 2.c of this Subsection.
 - a. Corrective work shall be accomplished by diamond grinding or by removal and replacement, at no cost to the Department.
 - b. Diamond grinding equipment used for surface correction shall be power driven, self-propelled units specifically designed to grind and texture pavements. The cutting head shall be at least 36 inches wide and consist of many diamond blades with spacers. The Engineer may approve equipment with a narrower width for irregular and confined areas which will not accommodate larger equipment and for bumps of limited number and area.
 - c. The Contractor shall re-test all corrected test sections with the non-contact profiler.
2. All bumps and dips, as defined in Subsection 602.05, Paragraphs 1.b and 1.c, shall be corrected until they are at or below the 0.30 inch limit. All dips shall be corrected by diamond grinding on either or both sides of the dip.
 - a. When the initial IRI of a test section is 93 in/mi or less, mandatory bump and dip correction is the only corrective work allowed for that section.
 - b. When the IRI of a test section exceeds 93 in/mi, the Contractor may perform voluntary corrective work in that section, in addition to mandatory bump and dip correction work.
 - c. When the IRI of a test section exceeds 124 in/mi, mandatory corrective work shall be performed to reduce the IRI of that section to a value of 124 in/mi or less. The Contractor may perform voluntary corrective work in that section, in addition to mandatory work.
 - d. Dip correction by diamond grinding shall not reduce the pavement thickness to less than the required plan thickness minus $\frac{1}{4}$ inch.
3. When pavement removal and replacement is used for correction, the Contractor shall furnish the replacement material and construction at no cost to the Department.
 - a. All replacement material shall meet the original specifications for the material removed.
 - b. Removal and replacement shall be for the full lane width for a distance determined by the Engineer.

- c. Replacement material must meet the same smoothness requirements as the removed pavement.

602.07 - Traffic Control

1. The Contractor shall provide all traffic control for smoothness testing and corrective work at no cost to the Department.

602.08 – Method of Measurement

1. The unit price of the accepted quantity of Portland cement concrete pavement in each profile test section shall be adjusted according to the schedule in Table 602.01, subject to the limitations in Paragraphs 2, 3 and 4 of this Subsection. Pavement sections excluded from this smoothness specification shall not qualify for incentive pay.

Table 602.01

<i>Payment Adjustment Schedule</i>	
IRI Inches Per Mile	Percent of Contract Prices
0 to 43	106
Greater than 43 to 56	104
Greater than 56 to 68	102
Greater than 68 to 93	100
Greater than 93 to 99	98
Greater than 99 to 105	96
Greater than 105 to 111	94
Greater than 111 to 117	92
Greater than 117 to 124	90
Greater than 124	Corrective work required

2. When the initial IRI of a test section is 93 in/mi or less, that value shall determine the percent of incentive pay for the section, except that any mandatory correction work performed in that section may increase the percent of pay up to the 106 percent level indicated in Table 602.01.
3. When the initial IRI of a test section is greater than 93 in/mi, mandatory or voluntary corrective work performed in that section may increase the percent of pay up to the 100 percent level indicated in Table 602.01.
4. When the initial IRI of a test section is greater than 124 in/mi, mandatory and voluntary corrective work performed in that section may increase the percent of pay up to the 100 percent level indicated in Table 602.01.

602.09 – Basis of Payment

1. The overall pay factor for the accepted quantity of Portland cement concrete pavement in all profile test sections shall be determined according to the formula in Table 602.02.

Table 602.02**Pay Factor Formula**

$$\text{PF} = \frac{A(1.06) + B(1.04) + C(1.02) + D(1.00) + E(0.98) + F(0.96) + G(0.94) + H(0.92) + I(0.90)}{A + B + C + D + E + F + G + H + I}$$

Where:

- A = Length of pavement with an IRI of 0 to 43 inches per mile.
- B = Length of pavement with an IRI greater than 43 to 56 inches per mile.
- C = Length of pavement with an IRI greater than 56 to 68 inches per mile.
- D = Length of pavement with an IRI greater than 68 to 93 inches per mile.
- E = Length of pavement with an IRI greater than 93 to 99 inches per mile.
- F = Length of pavement with an IRI greater than 99 to 105 inches per mile.
- G = Length of pavement with an IRI greater than 105 to 111 inches per mile.
- H = Length of pavement with an IRI greater than 111 to 117 inches per mile.
- I = Length of pavement with an IRI greater than 117 to 124 inches per mile.

2. The work of smoothness testing shall be paid for at the lump sum contract unit price. This price shall be full compensation for all smoothness testing as set forth in this specification.

CONCRETE PAVEMENT REPAIR

Section 605 of Standard Specifications is void and Superseded by the following.

I. Description

1. This work shall consist of repairing Portland cement concrete pavement at the locations shown in the contract or as designated by the Engineer. The work shall include removing poorly constructed or deteriorated concrete, disposing of the old concrete, preparation of the repair areas, and furnishing, placing, finishing, and curing the concrete for the repairs.

2. Concrete pavement repairs are grouped into 3 types based on the surface area of the patch (see Table 1). If a pavement failure extends across more than one lane, each lane will be counted as a separate repair.

Table 1
PCC Pavement Repair Groups

Type	Size
	<u>Square Yards or m²</u>
A	Less than 5
B	5 to 15
C	More than 15

3. Full depth pavement repair shall be constructed on the existing foundation course. The thickness of the new concrete pavement will be as shown in the contract or the thickness of the adjacent pavement, as appropriate.
4. Special Prosecution:
 - a. When performing concrete pavement repairs on 2-lane roadways, the Contractor shall have all lanes open to traffic before sunset and at times when the Contractor is not working. Where the pavement has been removed and the Contractor will be unable to complete the required patching in time for the concrete to obtain the full curing time required prior to opening the section of the road to traffic, the excavation shall be filled with a commercially available cold-mix bituminous mixture, or other suitable temporary patch material with a durable surface, as directed by the Engineer. The Contractor will be required to maintain normal traffic flow across these patches while they are in service. When it is necessary to use "temporary patches", they shall be removed, the excavation cleaned out, and the required permanent patch placed, within 48 hours unless otherwise directed by the Engineer. The temporary patches will be at no cost to the Department.
 - b. When performing concrete pavement repairs on multi-lane highways, the Contractor will be permitted to have one lane closed during the period of the repair work. Repairs that are not located behind concrete protection areas shall not be left open overnight. Where the pavement has been removed, and the Contractor is unable to complete the required patch before sunset, the Contractor shall fill the excavated area with either: (1) the appropriate patching concrete material for curing overnight, or (2) a suitable material with a durable surface. When it is necessary to use temporary patches, they shall be removed, the excavation cleaned out, and the required permanent patch placed, within 48 hours, unless otherwise directed by the Engineer. The temporary patches will be at no cost to the Department.

II. Material Requirements

1. Repairs shall be made with Class 47B-3500 or 47B HE-3500 concrete.
2. All materials shall be furnished by the Contractor and shall conform to the requirements in Table 2.

Table 2

Material Requirements	
Applicable Materials	Section*
Portland Cement Concrete	1002
Curing Compounds (Without Asphalt Overlay)	1012
Aggregates	1033
Fly Ash	1008
Curing Compounds (With Asphalt Overlay)	1013
Joint Sealing Filler	1014
Admixtures	1007
Water	1005
Epoxy Compounds & Adhesives	1018

* of the 2007 edition of the NDOR Standard Specifications for Highway Construction

III. Equipment

1. A mobile mixer conforming to the requirements of Section 1002 of the Standard Specifications may be used.
2. Adequate hand tools shall be provided, including an internal vibrator.
3. Screeds, either mechanical or hand operated, shall be used to finish the concrete except for small patches. The screeds shall be either a vibrating or roller type screed specifically designed for striking off concrete.
4. Internal vibrators shall meet the requirements of Section 601.
5. Drills for dowels or tie bars, shall be capable of drilling the appropriate sized hole parallel to the surface of the concrete and the longitudinal centerline within 1/8 inch.

IV. Construction Methods

1. Removal
 - a. The repair sections shall be removed to the lines designated by the Engineer. The Contractor shall remove the concrete pavement without damaging the adjacent concrete pavement. Damaged pavement shall be replaced to the satisfaction of the Engineer at no cost to the Department.

- b. The Contractor shall use a diamond blade to make a full-depth cut around the perimeter of the repair area.
- (1) All saw cuts made for full-panel removals shall be made along the existing joints.
 - (2) Partial-panel repairs, made on the side directly adjacent to other panels, shall be made along the existing joints.
 - (3) All saw cuts, made through the slab for partial-panel repairs, shall be parallel or perpendicular to the traveled way.
 - (4) Saw over-cuts shall be kept to a minimum. If saw over-cuts occur, they shall be thoroughly cleaned with compressed air to remove all dust, dirt, loose material and moisture. If the saw cut is within the slab, it shall be sealed with a Type IV, Grade 3 epoxy, per the manufactures requirements. If the saw cut is along an existing joint, it shall be sealed with hot pour joint sealant.
- c. The repair section shall be removed with minimum disturbance of the underlying foundation course. Any loosened foundation course shall be re-worked and compacted to the satisfaction of the Engineer.
- d. Full depth relief cuts (approximately 4 inches (100 mm) wide) may be made with a wheel cutter through the repair section provided that:
- The relief cutting operation is performed in a manner that minimizes the disturbance of the underlying foundation course material.
 - The relief cutting operations do not damage the adjacent pavement.
- e. The Contractor shall use hand or pneumatic tools to remove the concrete pavement. If the patch is a Full Depth Type C or a Full Depth Long Repair, then a drop hammer may be used to remove the pavement.
- f. The initial removal of any concrete pavement other than that described above shall be removed by means of a jackhammer not exceeding 35 pounds (16 kg). The repair sections shall be removed to the lines designated by the Engineer, including reinforcement that interferes with the operations. The cut-away repair section shall be removed with minimum disturbance of the underlying foundation course.
- g. The corners of the repair section shall be prepared with reasonably neat vertical surfaces using a 15-pound (maximum) chipping hammer.
- h. The Contractor shall remove and dispose of all old pavement, reinforcing steel, and all other materials that are removed and not identified for reinstallation.

2. Preparation

- a. Foundation Course Replacement shall consist of removing and disposing of foundation course (i.e., bituminous, crushed concrete or granular) that is fouled by the removal operation or judged unacceptable by the Engineer.
 - (1) The fouled or unacceptable foundation course shall remove and dispose of and replace with concrete of the same type used for the repair. The additional depth of concrete required shall be placed monolithically with the pavement repair concrete.
- b. The Contractor shall compact the foundation course under full depth patches to the maximum density achievable.
- c. Dowel bars and tie bars shall be anchored into the faces of the existing concrete pavement as designated in the contracts.
 - (1) A minimum of 2 tie bars shall be placed on each side of a full depth pavement repair as designated in the contract.
 - (2) The dowel bar holes shall be drilled at the same plane $\pm 1/8$ inch, at the locations and spacing shown in the contract.
 - (3) The tie bar holes can be drilled independently.
 - (4) The drilled holes shall be thoroughly cleaned with compressed air to remove all dust, dirt, loose material and moisture.
- d. After cleaning and prior to dowel or tie bar insertion, an application of grout or Type IV, Grade 3 epoxy shall be made at the back of the hole. The grout or epoxy shall be from the Approved Products List. Twist the dowel or tie bar one full turn during insertion to completely surround it with the grout or epoxy. Retention disks shall be placed on the bars as designated in the plans.
- e. Where the repair area is not bordered by existing concrete pavement, a form shall be used as the pavement edge to provide the same surface elevation and edge alignment as the existing pavement. The form shall be supported or braced in position to prevent movement during the placement and finishing of the concrete. Forms for concrete pavement repair shall conform to the requirements of Subsection 603.03.
- f. For the new matching transverse joints within the full-panel repairs of the existing doweled concrete pavement, dowel baskets shall be placed parallel to the joint, and the dowel bars shall be parallel to centerline.
- g. For the new matching transverse joints within the partial-panel repairs of the existing doweled concrete pavement, the dowel bars shall be placed parallel to centerline on chairs or with dowel baskets parallel to the joint and the dowel bars shall be parallel to centerline.

3. Placing and Finishing

- a. The foundation course shall be uniformly wetted before placing the concrete.

- b. The Contractor shall furnish and place the concrete. The concrete shall be handled and consolidated so there will be no separation of the aggregate and the mortar.
- c. An internal vibrator shall be used to consolidate the concrete.
- d. A vibrating screed shall be used on a full depth concrete repair that is 5 feet or wider to finish the concrete to the final elevation.
- e. Immediately after finishing the concrete, it shall be floated with a magnesium bull float. Repairs that replace existing tined pavement shall be hand tined. The new tining shall be parallel to the existing tining in the adjacent concrete pavement.
- f. The Contractor shall cut joints to match the existing pavement joints. Transverse joints shall be established by sawing to a minimum depth as shown in the contract.
- g. The Contractor shall edge the surface that abuts a transverse joint to provide a well 0.4 inch (10 mm) wide and 0.6 (15 mm) inch deep.
- h. The Contractor shall use an edging tool to finish all exterior edges of the new concrete.
- i. The Contractor shall apply curing compound to all concrete pavement repairs.
- j. White pigmented curing compound shall be applied to all exposed surface. The application rate shall be 1 Gal/150 SF.
- k. Class 47B-3500 (47B-25 MPa) concrete pavement repairs shall not be opened to traffic until the compressive strength reaches 3500 psi (25 MPa). Table 3 is a guide to the minimum time the 47B-3500 concrete will reach a compressive strength of 3500 psi.
- l. Concrete shall not be placed when ambient air temperature is expected to drop below 40°F (4°C) during the cure period.

Table 3

Class 47B-3500	
Minimum Ambient Air Temperature [°F (°C)]	Hours
Below 41 (5° C)	120
41 – 60 (5°-16°C)	72
Above 60 (16°C)	48

4. Joints
 - a. All sawcuts, transverse joints, and longitudinal joints shall be thoroughly cleaned with compressed air to remove all dust, dirt, loose material and moisture, and sealed with hot pour joint sealant s prescribed in Section 603 of the Standard Specifications.
 - b. Joints shall not be sealed until after any necessary diamond grinding corrective work is completed. Joint wells that are destroyed shall be re-constructed, and joints of insufficient depth shall be deepened prior to sealing.
5. Smoothness
 - a. The pavement elevation of repair areas shall be corrected in a manner that eliminates dips or bumps. Dips and bumps are defined as having a 1/8 inch or greater deviation using an approved 10 foot straightedge. If the repair will be the wearing surface, the correction shall be diamond grinding or replacement. If the repair will be overlaid, the correction shall be milling, diamond grinding or replacement. The condition of the adjacent pavement shall be considered when evaluating the 1/8 inch deviation requirement.
 - b. Disturbed or damaged areas in the existing surfaced shoulder resulting from the repair operation shall be repaired by the Contractor to the satisfaction of the Engineer at no additional cost to the Department.
6. All pavement markings removed or damaged as part of the repairs shall be installed in accordance with the contract.

V. Method of Measurement

1.
 - a. The quantity of each type of concrete pavement repair is measured in cubic yards (meters) of pavement replaced in each separate lane.
 - b. Concrete pavement repairs that adjoin full depth repair areas of varying widths in the same traffic lane which are situated such that the removals of the areas may be accomplished concurrently, shall be considered as a single repair. The total area of the adjoining areas shall be combined to determine the repair type as shown in Table 1.
2. "Foundation Course Replacement" will be measured by the cubic yard of foundation course replaced. Foundation Course Replacement" that is the result of fouling of the foundation course by the Contractor will not be measured for payment.

VI. Basis of Payment

- | 1. Pay Item | Pay Unit |
|--|--|
| Concrete Pavement Repair, Type A, Full Depth | Cubic Yard (CY)
[Cubic Meter (m ³)] |
| Concrete Pavement Repair, Type B, Full Depth | Cubic Yard (CY)
[Cubic Meter (m ³)] |
| Concrete Pavement Repair, Type C, Full Depth | Cubic Yard (CY)
[Cubic Meter (m ³)] |
| Concrete Pavement Repair, Full Depth Long Repair | Cubic Yard (CY)
[Cubic Meter (m ³)] |
| Foundation Course Replacement | Cubic Yard (CY)
[Cubic Meter (m ³)] |
2. a. The 28-day compressive strength of each day's production will be determined from cylinder strength tests for 47B concrete.
- (1) Payment shall be reduced by the amount prescribed in Table 603.03 of the Standard Specifications.
- (2) For 47B concrete, if the 28 day strength fails, the Contractor has the option to take 3 core samples at no additional cost to the Department. The average compressive strength of these cores will be used to determine the actual 28-day compressive strength of each day's production.
- (i) Cores must be taken within 45 days from the date the concrete was poured.
- (ii) The Engineer shall select the site where the cores will be taken.
3. "Foundation Course Replacement" not resulting from fouling of the foundation course by the Contractor will be paid for at the contract unit price per cubic yard for the item "Foundation Course Replacement". This price shall be full compensation for removing and disposing of the old foundation course, preparation of the subgrade, furnishing and placing the replacement concrete, and for all labor, equipment, tools and incidentals necessary to complete the work. Fouled foundation course removal and replacement, including the concrete, shall be performed at no cost to the Department.
4. The sealing of all random cracks or joints will not be measured and paid for directly but shall be considered subsidiary to the joint or pavement repair work being performed.
5. Payment is full compensation for all work prescribed in this Section.

SEEDING

Type "B"	Minimum Purity	Broadcast or Hydraulic Seeder Application Rate in lb. of	Approved Mechanical Drill Application Rate in lb. of Pure Live Seed/Acre
Perennial ryegrass – Linn	85		6
Slender wheatgrass	85		5
Kentucky fescue	85		1
Western wheatgrass – Arriba, Flintlock	85		6
Thickspike wheatgrass – Critana	85		2
Blue grama – NE, KS, CO	30		2.5
Buffalograss – Sharp's Improved, Bison, Texoka, Cody	80		4
Sideoats grama – Butte, El Reno, Trailway	75		4
Sand dropseed (Sporobolus cryptandrus)	75		0.2
Oats/Wheat*	90		16

*Wheat in the fall

All seed shall be origin Nebraska, adjoining states, or as specified. A Contractor proposing to use a substitute variety, or origin shall submit for the Engineer's consideration a seed tag representing the seed which shows the variety, origin and analysis of the seed.

Rate of application of commercial inorganic fertilizer shall be:

	Rate of Application per Acre
Available Nitrogen (N ₂)	32 or 36 lbs.
Available Phosphoric Acid (P ₂ O ₅)	92 or 96 lbs.

Rate of application of granular sulphur coated urea fertilizer shall be:

Nitrogen (Total Available)	0 lbs.
----------------------------	--------

The contractor may, at his option, apply granular urea formaldehyde in lieu of the sulphur coated urea fertilizer at the following rate:

Nitrogen (Total Available)	0 lbs.
----------------------------	--------

**PORTLAND CEMENT CONCRETE
(J-15-0914)**

Paragraph 1. of Subsection 1002.02 in the Standard Specifications is amended to include the following:

Concrete mixes will be in accordance of Table 1002.02.

Paragraph 3. of Subsection 1002.02 is void and superseded by the following:

3. Type IP and IT Interground/Blended cement shall be used for all classes of concrete except for pavement repair. Type IP and IT Interground/Blended cement shall meet all requirements of ASTM C 595. Pavement repair shall include Type I/II Portland Cement for Class PR1 Concrete and Type III Portland Cement shall be used in Class PR3 Concrete.

Tables 1002.02 and 1002.03 in Subsection 1002.02 are void and superseded by the following:

**ENGLISH
TABLE 1002.02**

Class of Concrete (1)	Base Cement Type	Total Cementitious Materials Min. lb/cy	Total Aggregate		Air Content % Min.-Max. (2)	Ledge Rock (%)	Water/Cement Ratio Max. (3)	Required Strength Min. psi
			Min. lb/cy	Max. lb/cy				
47B**	IP/IT*	564	2850	3150	6.5 - 9.0	-	0.45	3500
47B***		564	2850	3150	6.0 - 8.5	-	0.45	3500
47BD		658	2500	3000	6.0 - 8.5	30+3	0.42	4000
47B-HE		752	2500	3000	6.0 - 8.5	30±3	0.40	3500
BX ₍₄₎		564	2850	3150	6.0 - 8.5	-	0.45	3500
47B-OL		564	2850	3200	6.0-8.5	30±3	0.36	4000
PR1	I/II	752	2500	2950	6.0 - 8.5	30±3	0.36	3500
PR3	III	799	2500	2950	6.0 - 8.5	30±3	0.45	3500
SF ₍₅₎	I/II	589	2850	3200	6.0 - 8.5	50±3	0.36	4000

- (1) Each class of concrete shall identify the minimum strength requirement, per plans and specifications.
All classes of concrete shall be air-entrained and a water-reducing admixture shall be used per manufacture's recommendations.
- Class R Combined Aggregate shall use a mid-range water reducer admixture. The dosage shall be at the manufacture's recommendation and the Engineer may approve a low-range water reducer admixture.
- (2) As determined by ASTM C 138 or ASTM C 231.
FOR INFORMATION ONLY. The Contractor may develop a Quality Control Program to check the quantity of air content on any given project; such as, checking the air content behind the paver.
- (3) The Contractor is responsible to adjust the water/cement ratio so that the concrete supplied achieves the required compressive strength without exceeding the maximum water/cement ratio. The minimum water/cement ratio for any slip form concrete pavement is 0.38, unless the Contractor requests approval from the Engineer in writing to change the minimum water/cement ratio to 0.36.
- (4) For temporary surfacing, Type I/II cement is allowed.
- (5) Minimum Portland Cement shall be 564 lbs/cyds and the total Silica Fume added shall be 25 lbs/cyds.

(*). Refer to Subsection 1004.02 for material characteristics.

Lithium Nitrate may be used in place of Supplemental Cementitious Materials (SCMs), see Section 1007 of the Standard Specifications as modified in these Special Provisions.

(**) For slip form applications.

(***) For hand-pours and substructures applications.

Table 1002.03	
Table of Acceptable Concrete Class Substitutions	
Class Specified	Acceptable Class for Substitution
BX	47B, 47BD or 47B-HE
47B	47BD or 47B-HE

Paragraphs 5., 6., 7., 8., 9. and 10. of Subsection 1002.02 are void and superseded by the following:

5. Class PR1 and PR3 Concrete:
 - a. The calcium chloride for use in PR concrete shall be either:
 - (1) A commercially prepared solution with a concentration of approximately 32 percent by weight.
 - (2) A Contractor prepared solution made by dissolving 4.5 pounds of Grade 2 or 6.2 pounds of Grade 1 calcium chloride per gallon of water to provide a solution of approximately 32 percent by weight.
 - b. The 7.4 pounds of water in each gallon of solution shall be considered part of the total water per batch of concrete.
 - c. The calcium chloride solution shall be added, just prior to placement, at a rate of 0.375 gallons/100 pounds of cement (1.4 lb. calcium chloride per 100 lb. cement).
 - d. Class A, Flaked or Pellet Calcium Chloride shall be added at a rate not to exceed 2.0 percent of the weight of the cement for Grade 1, or 1.6 percent of the weight of the cement for Grade 2. Grade 1 Calcium Chloride purity is between 70 and 90 percent and Grade 2 Calcium Chloride is between 91 and 100 percent.
 - e. Where mixing trucks are used:
 - (1) For Class PR3 Concrete, calcium chloride shall be thoroughly mixed into the concrete before placement. The minimum mixing time is 2 minutes.
 - (2) For Class PR1 Concrete, calcium chloride shall be added first and then the concrete mixed at least 2 minutes or as required by manufacturer. Next, the Type F high range water-reducer admixture is added and the concrete is mixed an additional 5 minutes.
6. Class High Early (47B-HE) Concrete
 - a. High Early (47B-HE) concrete shall be cured as prescribed in Subsection 603.03, Paragraph 7. The Contractor shall take necessary curing measures so the required strength is achieved.
 - b. High Early concrete shall achieve a compressive strength of 3,500 psi at 48 hours after placement.

- c. The 48-hour compressive strengths shall be used to determine pay factor deductions for high early concrete in accordance with Table 603.03.
 - d. A non-calcium chloride accelerator shall be used when the ambient temperature at the time of the placement of concrete is 70°F or less.
 - e. When requested by the Contractor, the maturity method, as provided in NDR C 1074, may be used in lieu of the requirements of Subsection 603.03, Paragraphs 11.c. and d. to determine the strength of concrete pavement for the purpose of early opening to traffic and acceptance. Requests by the Contractor for use of the maturity method shall be on a project basis and shall be made in writing to the Engineer.
7. The yield of the concrete proportions shall be determined and adjusted by the Producer.
8. All Classes of Concrete with the exception of PR1 and PR3 shall have a Durability Factor not less than 70 and a mass loss not greater than five percent after 300 freeze/thaw cycles when tested in accordance with ASTM C 666. The freeze/thaw testing shall be conducted according to Procedure A.

Paragraphs 1. & 2. of Subsection 1002.03 are void and superseded by the following:

1. The Contractor shall identify the plant that will supply the concrete 14 days before use and be entirely responsible for its calibration, batching of concrete, aggregate and sampling of cement per NDR Sampling Guide.
- a. The Contractor shall be responsible for the following:
 - 1) Batching concrete.
 - 2) Contractor shall sample aggregate from the conveyor belt or stockpile. Gradations from a split sample shall be tested in accordance to Section 1033 and reported to the Engineer at the frequency required by the Materials Sampling Guide.
 - i. Contractor shall retain possession of the split samples on-site at the Contractor's facility until such a time as determined by the Engineer.
 - a. At the pre-construction meeting:
 - 1) Contractor shall determine the location of testing and report the names of the technician performing the sampling and testing.
 - 2) Engineer will notify the Contractor of the retrieval of the split samples.
 - ii. The Contractor shall split the sample, place the Department's split sample into a cloth bag and immediately seal the split sample with the provided security seal. The cloth sample bag shall be supplied by the Department.
 - iii. The sampling splitting and placement of the security seal of aggregate samples shall be witnessed by certified Department personnel.

- iv. Contractor shall secure the split sample using a consecutively numbered security seal of 75 pounds breaking strength provided by the Department. The Contractor shall use the consecutively numbered security seals to identify and track each Aggregate Class. Samples that are not consecutively numbered will be investigated for custody of the sample and the Engineer may cease production until it is determined what action will be required.
 - a. The Contractor shall report the security seal tracking number with the split sample gradation.
 - b. The following training shall be required for personnel who oversee the batching of the concrete:
 - 1) Concrete Technician Personnel
 - i. Concrete Plant Technician
 - 2) Portland Cement Sampler
 - i. NDR Portland Cement Sampler
- 2. Portland Cement Concrete shall be supplied by certified Ready Mix Plants that are in compliance with the requirements in the *Quality Control Manual*, Section 3, -- Certification of Ready Mixed Concrete Production Facilities published by the National Ready Mixed Concrete Association. Refer to NDR Material Sampling Guide for the policy on stationary and portable plants.

Paragraph 4. of Subsection 1002.03 is void and superseded by the following:

- 4. a. Mix times shall meet the requirements of ASTM C 94. Mixing time tests shall be repeated whenever the concrete appearance indicates that mixing was inadequate.
- b. Batch plants that are transporting the concrete in non-agitating trucks, the mixing time will not be less than 60 seconds, and for agitating trucks, the mixing time will not be less than 45 seconds.
- c. The Certification of stationary and portable ready mix plants will conform to the tests that are required in the NDR Materials Sampling Guide.

Paragraph 6. of Subsection 1002.03 is void and superseded by the following:

- 6. Batch tickets shall be prepared as prescribed in the National Ready Mixed Concrete Association's *Quality Control Manual*. The Contractor shall keep all gradations and batch tickets until final acceptance by the Department. Projects that have less than 200 cubic yards of concrete placed will be allowed to have hand written tickets. For projects greater than 200 cubic yards, hand written tickets will be at the Engineer's discretion. The concrete batch tickets shall show batch weights, aggregate moisture (shall be tested daily and moisture probes are allowed), admixtures used, water, and mix design calculations. A copy of the batch ticket shall be given to the Engineer upon delivery of concrete.

Paragraph 8. of Subsection 1002.03 is void and superseded by the following:

8. Coarse aggregate and aggregate from a dry pit shall be uniformly saturated with water before it is used. The wetting shall begin 24 hours prior to the concrete mixing to allow complete saturation.

Paragraph 13.a. of Subsection 1002.03 is void and superseded by the following:

13. a. The quantity of water shall be determined by the Contractor. The minimum quantity of water should be used which will produce required workability. Any additional water used to rinse the charging hopper and fins after the batching of concrete is allowed. This water must be estimated and recorded on the batch ticket.

Subsection 1002.04 is void and superseded by the following:

1. Class 47B Concrete Mix Design Submittal:
 - a. The Contractor shall submit the Concrete Mix Design Worksheet consisting of design mix proportions, testing of mix design from a minimum of 4 cubic yards and aggregate data for 47B class of concrete being placed on the project.
 - (1) All testing must be performed by a qualified laboratory found on the NDR's Material and Research website, under the *Nebraska Qualified Consultant & LPA Laboratories* and submitted to the Engineer.
 - (2) The Concrete Mix Design shall be submitted to the Engineer 4 weeks prior to any concrete being placed on the project.
 - (3) The Concrete Mix Design shall not be paid for directly by the Department and shall be subsidiary to items which direct payment is made.
 - (4) Concrete shall not be placed on the project before the Concrete Mix Design Worksheet has been reviewed and approved by the Engineer.
 - b. The Contractor shall submit the Concrete Mix Design Worksheet to the Engineer. Email submissions are preferred but will be accepted by fax or postal mail.
 - (1) Contractor's Mix Design Worksheet can be found on the Materials and Research website. The submitted Mix Design Worksheet shall include the following:
 - Contractor Name
 - Project Number
 - Date
 - Location of ready mix or central mix plant
 - Date submitted
 - Signature of Contractor representative

- (2) Material Source Information.
 - Cement Manufacturer
 - Type of Interground/Blended Cement
 - Type of Admixtures
 - Aggregate Pit and Quarry location
- (3) Specific Gravity of each individual aggregate source.
- (4) Sand Equivalent for dry pit sand-gravel aggregate.
- (5) Combined Aggregate percent passing as described on Table 1033.03C.
- (6) Contractor's Target combined aggregate gradation percent passing.
 - (i) The Contractor's required worksheet can be found on the Materials and Research website.
- (7) Testing of Mix Design:

The mix design shall show the weights of all ingredients including Interground/Blended cements, aggregates, water, admixtures types and water cement ratio.

- Temperature of concrete at time of sampling, ASTM C 1064.
 - The air content of plastic concrete, ASTM C 231.
 - Weight per cubic foot, Yield, ASTM C 138. The relative Yield shall be a minimum of 97%.
 - Compressive strength shall be performed with a minimum of three averaged specimens at 7-day and 28-day, ASTM C 39. The minimum 28-day compressive strength shall be 3500 psi.
- (8) Traditional 47B Mix Design is defined as an IP(25) cement, 70 percent Class B Aggregate and 30 percent Class E Aggregate may be exempt from the concrete testing described in Paragraph 1.(b)(7). All other requirements shall be included in the Concrete Mix Design Report.

- c. The PCC Engineer will notify the Contractor of the mix design approval for Class 47B Concrete. Approval of the mix design does not alleviate the Contractor of the responsibility of the in-place concrete. The Contractor may adjust admixtures, water cement ratio, vibrator frequency, etc., as needed in accordance to the specifications.
- d. The Contractor shall submit a new concrete mix design worksheet meeting the above requirements when a change occurs in the source,

type, or proportions of cements or aggregates; unless otherwise approved by the Engineer.

2. The quantity of water to be used shall be determined by the Contractor. It shall not be varied without the Engineer's consent.
3. If the concrete mixture is excessively wet causing segregation, excessive bleeding, excessively dry or any other undesirable condition, the concrete shall be rejected. At the option of the Engineer, slump tests may be performed to determine the consistency.
4. Concrete which has developed initial set before it is consolidated and finished shall be rejected.
5.
 - a. If false set is encountered, the batching operation shall be stopped until the problem is resolved.
 - b. Each batch must be mixed or agitated for at least 3 additional minutes after observing the false set and the concrete must be of satisfactory consistency.
6. Compressive strength tests shall be made in accordance with ASTM C 39.
7. Concrete shall be sampled as prescribed in the NDR *Materials Sampling Guide*. Samples shall be taken at the point of placement, never before the discharge from the last conveyance.
8. Aggregate Acceptance, Verification, Sampling and Testing:
 - a. The aggregate will be accepted based on the Contractor's testing results except as noted below.
 - b. The aggregate verification sampling and testing by the Department will be randomly selected and tested according to subplot sizes in Table 1002.05.

Table 1002.05

Aggregate Class	Lot	Sublot
E and F	3000 tons	1000 tons
A,B and C	6000 tons	2000 tons
R	3000 tons	1000 tons

- c. The results of Contractor split sample will be verified by the Department's verification tests. Any samples outside of the tolerances as specified according to the *Materials Sampling Guide*, Section 28 under the *Acceptable Tolerance Limits for Independent Assurance* will result in an Independent Assurance (IA) review of testing and may result in the Department test results being applied.
- d. On any given Lot, if the results of the gradation from the verification test are within Department's specification, the Contractor's results will be used for the entire lot. On any given Lot, if the gradations results from the

verification test are outside Department's specification, further investigation will be initiated by the Engineer for that subplot. Any or all of the remaining Department subplot samples may be tested and the Department subplot test results may be applied to the respective subplot and the acceptance will apply.

- e. When verification tests are within testing tolerance but results show a consistent pattern of deviation from the split sample results, the Engineer will exercise one or more of the following:
 - Cease production.
 - Request additional verification testing.
 - Initiate a complete IA review.

- f. Independent Assurance (IA) Review of Testing:
 - 1) The Contractor shall allow the Department personnel access to the Contractors' laboratory to conduct IA review of the technician testing procedures and apparatus. Any deficiencies discovered in the Contractor's testing procedures will be reported to the Contractor and corrected by the Contractor.

 - 2) During the IA review, the Department personnel and the Contractor shall split a sample for the purpose of IA testing. The samples selected will be tested in the Department's Branch Laboratory. Any IA test results found to be outside of defined testing tolerances as stated in Paragraph 8.c. of Subsection 1002.04 will be reported to the Contractor. The Contractor shall immediately correct any deficiencies found during the IA review.

 - 3) If the project personnel and the Contractor cannot reach agreement on the accuracy of the test results, the Department Central Laboratory will be asked to resolve the dispute, which will be final. All dispute resolutions will be in accordance with the Quality Assurance Program requirements in the NDR's Materials Sampling Guide.

PORTLAND AND INTERGROUND/BLENDED CEMENT (J-15-0214)

Section 1004 in the Standard Specifications is void and superseded by the following:

1004.01 – Description

- 1. Portland cement is the binder in concrete, locking the aggregate into a solid structure. It is manufactured from Lime, Silica, and Alumina (with a small amount of plaster of Gypsum).

- 2. Equivalent alkali referred to herein is hereby defined as the sum of the Sodium Oxide (Na_2O) and the Potassium Oxide (K_2O) calculated as Equivalent Alkali $\text{Na}_2\text{O}_e = \text{Na}_2\text{O} + 0.658 \text{K}_2\text{O}$.

3. Interground and Blended cements consist of intimate and uniform intergrinding or blending of Portland cement clinker, Slag cement, Pozzolan and/or Limestone.

1004.02 – Material Characteristics

1. Type I, Type II, Type I/II and Type III Portland cement shall conform to the requirements in ASTM C 150 with the following additional requirements:
 - a. Portland cement shall not contain more than 0.60 percent equivalent alkali.
 - b. Processing additions may be used in the manufacture of the cement, provided such materials have been shown to meet the requirements of ASTM C 465 and the total amount does not exceed 1 percent of the weight of Portland cement clinker.
2. Interground and Blended Cement shall conform to the requirements in ASTM C 595 with the following additional requirements:
 - a. Interground/Blended cement (Type IP)
 - (1) For Type IP(25) shall be composed of Class F fly ash or Class N pozzolan replacement shall be 25% \pm 2%.
 - (2) For Type IP(20) shall be composed of Class F fly ash or Class N pozzolan replacement shall be 20% + 2%.
 - b. Interground/Blended cement (Type IT)
 - (1) For SCMs, Slag cement and Limestone, the maximum replacement by weight shall be 40%. The manufacturer has a production tolerance of \pm 2% from the proposed replacement.
 - (2) For Slag Cement, the maximum replacement shall be 20% or less when incorporated into the final Interground/Blended cement.
 - (3) For Limestone cement, the replacement range shall be from 5.1% to 10.0% when incorporated into the final Interground/Blended cement.
 - c. No additional SCMs, Slag cement and Limestone will be added at the batch plant.

1004.03 – Procedures

1. The Contractor shall provide adequate protection for the Portland and Interground/Blended cement against dampness.
 - a. Portland and Interground/Blended cement shall be hauled or stored in railroad cars, dry bulk trailers or in suitable moisture-proof buildings.
 - b. The use of tarpaulins for the protection of the Portland and Interground/Blended cement against moisture will not be allowed.

2. No Portland and Interground/Blended cement which has become caked or lumpy shall be used.
3. Portland and Interground/Blended cement which has been spilled shall not be used.
4. Accepted Portland and Interground/Blended cement which has been held in storage at the concrete mix plant more than 90 days shall be retested.
5. Portland and Interground/Blended cement coming directly from the manufacturer shall not be used until the temperature is 150°F or less.
6. Portland cement having false set when tested in accordance with in ASTM C 150 will not be used.

1004.04 – Acceptance Requirements

1. For Department projects, Portland and Interground/Blended cements must be on the NDR Approved Product List (APL).
2. The Contractor shall submit any new Portland and Interground/Blended cements to the Engineer to be approved for the APL with the following:
 - a. Material source information:
 - 1) Mill Location
 - 2) Type of Portland and Interground/Blended cements
 - 3) Grinding Period
 - 4) Associated Manufacture Product Name
 - 5) Provide source and type of each SCMs and/or Slag Cement used for final product.
 - (i) The Department will allow the use of ASTM C 1697.
 - a. When two or more SCMs and/or Slag Cement are pre-blended, the Contractor shall report chemical composition analysis of the final blend.
 - b. The final blend shall be reported as per ASTM C 1697, Paragraph 4.
 - 6) Portland cement shall conform to ASTM C 150.
 - 7) Interground/blended cements shall conform to ASTM C 595.
 - 8) Provide total cementitious materials replacement per ASTM C 595.
 - 9) Report test results per ASTM C 1567 at 28-days.

3. Alkali Silica Reaction Requirements and Testing:
 - a. Interground/Blended cement shall be tested according to the provisions of ASTM C 1567.
 - (1) The mortar bars shall be composed of Type IP or IT Interground/blended cement and sand and gravel from an approved Platte River Valley-Saunders County source.
 - i. When Elkhorn River-Madison County source or an out of state aggregate source and type IP(20) or IT cement is being used on a project, the Elkhorn River or an out of state aggregate source shall be used in lieu of the Platte River Valley-Saunders County source.
 - ii. When Contractor proposes a change of aggregate source, then the new aggregate source shall be tested by ASTM C 1567.
 - (2) The mortar bars for the ASTM C 1567 shall not exceed 0.10% expansion at 28 days.
 - i. To accommodate precision within multi-laboratory testing, expansion up to and including 0.13% will be accepted for use. If the expansion is above 0.13%, the material is noncompliant. If tolerance problems are not corrected within 30 days following notification, the Interground/blended cement in question will be removed from the NDR's APL.
4. Portland and Interground/Blended cements will be placed on NDR's APL based on the conformance with the NDR's Acceptance Policy Portland and Interground/Blended Cements.

1004.05 - Sampling and Testing Requirements

1. All Portland and Interground/Blended cements shall be sampled and tested at the rate as described in the NDR's Materials Sampling Guide.
 - a. The Department will inform the Contractor when a sample is required.
 - b. A sample shall be taken by a Contractor's Certified Portland Cement Sampler and must be under the supervision of Department certified personnel.
 - c. The sample shall be taken at the plant from a bulk shipment of a rail car, dry bulk trailer, batch plant silo or from the line between the bulk truck and the silo. Upon sampling, the Department will take immediate custody of the sample.
 - d. When Elkhorn River aggregate- Madison County source or an out of state aggregate source and type IP(20) or IT cement is being used on a project, the Elkhorn River or an out of state aggregate source shall be used in lieu of the Platte River Valley aggregate source.
2. Noncompliant material from the mill, terminal or project will be temporarily removed from the Approved Products List pending further investigation.
3. If the noncompliant Portland or Interground/Blended cement is removed from the Approval Products List, all shipments from the supplier will be held until the investigation

of the failing samples have been completed by the NDR Materials and Research Division. These procedures shall be in accordance with this provision.

WATER FOR CONCRETE (J-15-0214)

Section 1005 in the Standard Specifications is void and superseded by the following:

1005.01 – Description

1. Water shall be free from objectionable quantities of oil, acid, alkali, salt, organic matter, or other deleterious materials and shall not be used until the source of supply has been approved.
2. Wash water from the mixer washout may be used only with the Engineer's approval. Use of wash water will be discontinued if undesirable reaction with admixtures or aggregates occurs.

1005.02 – Material Characteristics

1. Water which contains more than 0.25 percent total solids by weight shall not be used.
2. When required by the Engineer, the quality of mixing water shall be determined by NDR C 114, NDR T 290, NDR D 512, NDR C 1602, ASTM C 31, ASTM C 109, ASTM C 191, and ASTM C 1603.
3. Upon written request by the concrete producer and approval by Materials and Research, the concrete producer may utilize up to 10% wash water for batching all classes of concrete with the following conditions:
 - a. Wash water shall conform to the requirements in NDR's Material Sampling Guide under Policy for Certification of Ready Mix Plants.
 - b. Wash water must be clarified wash water that has been passed through a settling pond system.
 - c. Wash water must be scalped off of a settling basin that has been undisturbed for a minimum of 12 hours.
 - d. Wash water must be metered into each load.
 - e. Wash water quantities shall be shown on the batch ticket.

**CALCIUM CHLORIDE
(J-15-0214)**

Section 1006 of the Standard Specifications is void and superseded by the following:

1006.01 – Description

Calcium Chloride shall be Type S (Solid) or Type L (Liquid). Calcium Chloride can be used for; but not limited to, dust control and acceleration of the set of concrete.

1006.02 – Material Characteristics

The requirements for calcium chloride shall be tested in accordance with ASTM D 98.

1006.03 – Acceptance Requirements

Acceptance shall be based on requirements contained in the NDR Materials Sampling Guide.

**SECTION 1007 -- CHEMICAL ADMIXTURES
(J-15-0214)**

Section 1007 in the Standard Specifications is void and superseded by the following:

1007.01 -- Description

1. Admixtures are materials added to Portland cement concrete to change characteristics such as workability, strength, permeability, freezing point, and curing.
2. The Department's concrete admixture types are:
 - a. Type A - Water-Reducing Admixture - An admixture that reduces the quantity of mixing water required to produce concrete of a given slump.
 - b. Type B - Retarding Admixture - An admixture that slows the setting of concrete.
 - c. Type C - Accelerating Admixture - An admixture that speeds the setting and early strength development of concrete.
 - d. Type D - Water-Reducing and Retarding Admixture - An admixture that reduces the quantity of mixing water required to produce concrete of a given slump and slows the setting of concrete.
 - e. Type E - Water-Reducing and Accelerating Admixture - An admixture that reduces the quantity of mixing water required to produce concrete of a given slump and speeds the setting and early strength development of concrete.
 - f. Type F - Water-Reducing, High Range Admixture - An admixture that reduces the quantity of mixing water required to produce concrete of a given slump by 12 percent or greater.

- g. Type G - Water-Reducing, High Range and Retarding Admixture - An admixture that reduces the quantity of mixing water required to produce concrete of a given slump by 12 percent or greater and slows the setting of concrete.
- h. Air-Entraining - An admixture that encapsulates air in the concrete.
- i. Lithium Nitrate – An admixture used to control the Akali Silica Reaction (ASR) in concrete.

1007.02 -- Material Characteristics

- 1. Type A through G admixtures shall meet the requirements in ASTM C 494.
- 2. Air-entraining admixtures shall meet the requirements in ASTM C 260.
- 3. Use of admixtures other than those cited may be requested by the Contractor.
- 4. Admixtures shall not contain more than 1 percent of chlorides calculated as calcium chloride unless specified otherwise in the Specification.
- 5. Admixtures shall be used at the manufacturer's recommended dosage rates.
- 6. The air-entraining admixture characteristics shall produce concrete with satisfactory workability and total air content as prescribed in Table 1002.02.
- 7. a. When using the Lithium Nitrate admixture, the Contractor shall submit to the Engineer:
 - (i) A five pound sample of Portland cement that will be used on the project.
 - (ii) The Manufacturer's method for determining the recommendation for the required dose rate based on the equivalent alkali content.
 - (iii) Water content of the Lithium Nitrate admixture solution.
- b. The Engineer will report the equivalent alkali content to the Contractor. The Contractor shall use the reported equivalent alkali content to determine the required dose rate based on the manufacturer's recommendation.

1007.03 -- Procedures

- 1. The process for adding admixtures to a ready mix truck on the project site involves positioning the load of concrete up to the truck chute, stopping short of discharge.
 - a. The admixture is then poured over the surface of the concrete and mixed for at least 5 minutes.
 - b. No more than 1.3 gallons of water shall be used to rinse the admixture from the fins and top chute. This water must be shown on the proportioning report and shall not exceed the water cement ratio.
 - c. When Lithium Nitrate is used, the portion of the admixture that is water will be shown on the proportioning report and shall not exceed the water cement ratio.
 - d. The Contractor is responsible for the addition of the admixture.

2. a. If the air content is less than the minimum specified, addition of air-entraining admixtures is allowed.
- b. The Contractor shall take measures based on manufacturer's recommendations, that are within compliance of NDR Specifications, to bring the load of concrete into NDR prescribed limits according to Table 1002.02.
- c. If the air content is then outside the limits in Table 1002.02, the load of concrete shall be rejected.

1007.04 -- Acceptance Requirements

1. a. Approved chemical admixtures are shown on the NDR Approved Products List.
- b. Admixture approval shall be based upon annual certifications and certified test results submitted to the NDR Materials and Research Division.
2. The admixture must be essentially identical in concentration, composition, and performance to the admixture tested for certification.
3. Admixtures not identified on the NDR Approved Products List may be used under the following conditions:
 - a. A certificate of compliance and certified test results must be submitted to the NDR Materials and Research Division and approval for use must be given by the NDR Materials and Research Division.

**SILICA FUME
(J-15-0307)**

Paragraph 2 of Subsection 1009.03 in the Standard Specifications is void and superseded by the following:

2. Silica fume shall be protected from temperatures in excess of 90°F (32°C).

**LIQUID MEMBRANE-FORMING COMPOUNDS FOR CURING CONCRETE
(J-15-0307)**

Subsection 1012.03 in the Standard Specifications is void and superseded by the following:

1012.03 – Acceptance Requirements

1. All curing compounds to be approved must be from the current calendar year with no carry-over from the previous years.
2. Approved compounds are on the NDR Approved Products List.
3. Products not on the NDR Approved Products List shall be sampled and tested in accordance with requirements of the NDR Materials Sampling Guide.

BITUMINOUS LIQUID COMPOUNDS FOR CURING CONCRETE (J-15-1007)

Section 1013 in the Standard Specifications is void and superseded by the following:

1013.01 – Description

The compound shall consist essentially of an asphaltic base and shall be of a consistency suitable for spraying at temperatures existing at the time of construction operations. It shall form a continuous, uniform film. It shall be free of precipitated matter caused by conditions of storage or temperature. The compounds shall be relatively nontoxic.

1013.02 – Material Characteristics

- a. When tested in accordance with AASHTO T 155, the loss of water shall not be more than 0.11 lb/ft² (0.55 kg/m²) of surface area at 3 days, unless otherwise specified by the Engineer.
- b. The Contractor has the option of using bituminous tack coat. The tack coat shall conform to all requirements of Section 504.

1013.03 – Acceptance Requirements

Products shall be sampled and tested in accordance with requirements of the NDR Materials Sampling Guide.

JOINT AND CRACK SEALING FILLER (J-15-0813)

Section 1014 in the Standard Specifications is void and superseded by the following:

1014.01 – Description

Joint sealing filler shall be either a cold applied silicone product or an asphalt product (hot pour) conforming to the requirements of this Section. The type of joint filler to be used shall be as specified in the plans or special provisions. If not specified, any of the joint sealing fillers in this Section may be used.

Crack sealing filler shall be a hot pour sealer conforming to the requirements of this Section.

1014.02 -- Material Characteristics

1. NE-3405 and NE-3405LM (hot pour)
 - a. NE-3405 joint and crack sealer shall conform to the requirements of ASTM D6690, Type II. The material shall conform to the requirements of Table 1 with the following exception:
 - (i) The test of Bond, non-immersed, ASTM D5329, 3 specimens through 3 cycles shall be run at 0°F (-18°C), 100% extension.

- b. NE-3405LM (Low Modulus) joint and crack sealer shall conform to the requirements of ASTM D6690, Type IV. The material shall conform to the requirements of Table 1.
- c. The test of Bond, non-immersed, ASTM-D5329, will be tested on concrete blocks that will be constructed by the NDR Concrete Laboratory. The concrete blocks will be made of a 47B concrete mixture as prescribed in Section 1002 in the NDR Standard Specifications. The design is amended so that no fly ash is used in the mixture. All other specifications for Portland Cement Concrete apply.
- d. Sample conditioning, preparation and heating shall be in accordance with ASTM D 5167 with the following exceptions:
 - (i) The following sentence of Section 8.1.2, "Also, if present, remove container liner by cutting it away", is void and superseded by the following:

"Also, if present, as much of the polyethylene bag as possible, shall be removed by cutting it away. Wholly-meltable type container in contact with the sample section shall be left in place."
 - (ii) The last sentence of Section 8.1.2 "Solid Materials" is void and superseded by the following:

The entire vertical section which has been cut, shall be placed into the pot for melting.
 - (iii) The Section of 8.2.2.1 "Solid Materials" is void.
 - (iv) The Section of 8.2.3 is void and superseded by the following:

After the solid segment is added to the melter, the material shall be allowed to minimally melt to a uniform viscous state suitable for the installation of the stirrer or paddle. The sample shall then be stirred for one full hour. The oil bath temperature shall be regulated to bring the material to the maximum heating temperature within the one hour of stirring.
 - (v) The Section of 8.2.4.1 is void and superseded by the following:

During the one full hour of stirring, check the temperature of the material at maximum 15 minute intervals using a Type K thermocouple with the calibration verified in accordance with Section 6.1.7 to ensure conformance with specified temperature requirements. Stop the mechanical stirrer when measuring temperatures. If material temperatures ever exceed the maximum heating temperature, or ever drop below the minimum application temperature after the maximum heating temperature was reached, discard the sample and re-do the heating. Maintain appropriate records of times and temperatures to verify conformance with specification requirements.

- (vi) The Section of 8.2.4.2 is void.
- e. ASTM D 5329 shall include the following changes:
 - (i) Sections 6.4 and 12.4 "Specimen Preparation" shall have the reference of "177 ml (6 oz.)" replaced with "3 oz."
 - (ii) Section 6 "Cone Penetration, Non-Immersed" shall be superseded with the following exceptions:
 - 1. Section 6.5 "Procedure" is void and superseded by the following:

Place the specimen in a water bath maintained at 77 +/- 0.2°F (25 +/- 0.1°C) for two hours immediately before testing. Remove the specimen from the bath and dry the surface by shaking gently to remove free water from the surface of the specimen. Using the apparatus described in Section 6.3, make one determination at or near the center of the specimen. Take care to ensure the cone point is placed on a point in the specimen that is representative of the material itself, and is free of dust, water, bubbles, or other foreign material.
 - 2. Section 6.6 "Report" is void and superseded by the following:

Record the value as penetration of the specimen in dmm units.
 - (iii) Section 12 "Resilience" shall be superseded with the following exceptions:
 - 1. Section 12.5 "Procedure", void the sentence "Make determinations at three points equally spaced from each other and less than 13mm (½ inch) from the container rim" and supersede with the sentence "Make one determination at or near the center of the tin."
 - 2. Section 12.6 "Report" is void.

2. Silicone Joint Sealer (cold applied)
 - a. Silicone joint sealers may be either self-leveling or non-sag and shall meet the requirements in Table 1014.01.

Table 1014.01

Silicone Joint Sealer Requirement		
Property	Requirement	Test
As supplied:		
Specific Gravity	1.010-1.515	ASTM D792
Work Time, minimum	10 minutes	
Tack-Free, at 25°C	20-360 minutes	
Cure Time, at 25°C, maximum	14 days	
Full Adhesion, maximum	21 days	
As cured, at 25°C + 1.5		
Elongation, minimum	800%	ASTM D412
Durometer		
Non-Sag, Shore A	10-25	ASTM D2240
Self-Leveling, Shore 00, minimum	40	ASTM D2240
Joint Movement Capacity	+100% to -50%	ASTM C719
Tensile Stress, at 150% Elongation	45 psi	ASTM D412

1014.03 -- Packaging

1. NE-3405 and NE-3405LM
 - a. The joint and crack sealer can be packaged in either cardboard box of wholly-meltable type containers.
 - (i) Cardboard box containers shall be manufactured from double wall kraft board producing a minimum bursting test certification of 350 PSI (241 N/cm²) and using water-resistant adhesives. The use of metal staples or fasteners of any kind will be prohibited for closing the lids of the boxes. Tape or other like material is acceptable.
 - a. The joint and crack sealer shall be in meltable [300°F (149°C)] polyethylene bag(s).
 - (ii) Wholly-meltable type containers, and any of their components, shall be fully meltable and integrational with the joint and crack sealer by the time the manufacturer's minimum application temperature is reached.
 - a. The wholly-melted and integrated container must not adversely affect the test specifications of the joint and crack sealer.
2. Silicone Joint Sealer
 - a. Each container shall include information regarding manufacturer and product name.

1014.04 -- Acceptance Requirements

1. NE-3405 and NE-3405LM
 - a. Acceptance of the manufactured material is based on pre-approval by either on or off-site sampling. Acceptable hot pour sealant lots are listed on the NDR Approved Products List.
 - (i) NDR on-site field sampling shall be in accordance with the NDR Materials Sampling Guide.
 - (ii) Off-site (Proxy) sampling shall be in accordance with ASTM D 6690.
 1. Proxy sampling shall be overseen by an outside party approved by the NDR, preferably another DOT Agency. Proxy samples shall include a manufacturer's Certificate of Compliance. Proxy samples shall also include a dated signature of origin by the Representative that is not affiliated with the manufacturer, and can either be on the Certificate of Compliance, or separate letter.
 2. For convenience in both sampling and shipping samples, sample containers smaller than a manufacturer's usual production containers are allowed, as long as the sample is 1500 grams min.
 3. Samples shall be sent to the NDR Bituminous Laboratory, or alternatively, sent to an NDR-approved independent laboratory for testing which will be at no cost to the Department. If a NDR-approved independent laboratory will be used for testing purposes, the NDR Bituminous Laboratory must be notified so that NDR concrete blocks for Bond testing can be sent to it.
2. Silicone Joint Sealer
 - a. Acceptance of applied silicone joint sealers shall be in accordance with the NDR *Materials Sampling Guide*.
 - b. Acceptable silicone joint sealer manufacturer products are listed on the NDR Approved Products List.
 - (i) For products that are not listed, approval may be based upon test results from an independent laboratory submitted to the NDR Concrete Materials Section by the manufacturer, and testing by the NDR. Approval must be made prior to product use.

EPOXY COMPOUNDS AND ADHESIVES (J-15-0308)

Section 1018 in the Standard Specifications is void and superseded by the following:

1018.01 – Description

This specification provides requirements for two-component, epoxy-resin bonding systems for use in non-load bearing applications and resin adhesives for application to Portland cement concrete.

1018.02 – Material Characteristics

1. Epoxy-resin bonding systems shall conform to the requirements of ASTM C 881. Approved systems are shown on the NDR Approved Products List.
2. The classification of Epoxy-Resin Bonding Systems is as follows:
 - a. Type I For use in non-load bearing applications for bonding hardened concrete and other material to hardened concrete.
 - Type II For use in non-load bearing applications for bonding freshly mixed concrete to hardened concrete.
 - Type III For use in bonding skid resistant materials to hardened concrete, and as a binder in epoxy mortars or epoxy concretes.
 - b. Grade 1 Low viscosity.
 - Grade 2 Medium viscosity.
 - Grade 3 Non-sagging consistency.
 - c. Class A For use below 40°F (4°C); the lowest allowable temperature to be defined by the manufacturer of the product.
 - Class B For use between 40°F and 60°F (4°C and 15°C).
 - Class C For use above 60°F (15°C); the highest allowable temperature to be defined by the manufacturer of the product.
 - Class D For use between 40°F and 65°F (4°C and 18° C).
 - Class E For use between 60°F and 80°F (15°C and 26°C).
 - Class F For use between 75°F and 90°F (24°C and 32°C).

1018.03 – Procedures

1. The compounds shall be of the type and grade specified in the plans or as directed by the Engineer.

2. The class of the compounds shall be selected for use according to climatic conditions at the time of application.
3. All bonding surfaces shall be clean and free of all oil, dirt, grease, or any other materials which would prevent bonding.
4. Mixing and application shall be in strict accordance with the manufacturer's instructions.

1018.04 – Acceptance Requirements

1. Epoxy-resin bonding systems and resin adhesives approved for use are shown on the NDR Approved Products List.
2. Epoxy-resin bonding systems that are not on the NDR Approved Products List may be accepted based on a manufacturer's certificate of compliance.

DEFORMED METAL CENTER JOINT AND METAL KEYWAY (J-15-0307)

Paragraph 1 a. of Subsection 1027.01 in the Standard Specifications is void and superseded by the following:

a. Metal Center Joint:

Metal center joint sections shall be manufactured from sheets no less than 18 gauge [0.05 inch (1.3 mm)] thick and shall be of the size and trapezoidal shape shown in the plans. The sections shall be punched along the centerline of the narrow face of the trapezoid to admit the tie bars required by the plans and also at intervals of not greater than 2 feet (600 mm) to receive pins that are driven vertically into the subgrade to support the metal center joint.

AGGREGATES (J-15-0914)

Subsection 1033.01 is amended to include the following paragraphs and Subsection 1033.02, Paragraphs 1 and 3. of the Standard Specifications is void and superseded by the following:

1033.01 – Description

This combined aggregate gradation using Class R aggregate is to optimize aggregate blends utilizing more locally available materials.

Achieving a uniform gradation for Class R may require the use of two or more different aggregates. It is the responsibility of the contractor to consider additional material characteristics; such as, but not limited to particle shape, cubicity, angularity, etc., when designing a mix.

1033.02 -- Material Characteristics**1. Sampling and Testing Procedures:**

All materials shall be sampled and tested in accordance with Table 1033.01. All material source locations and quarries must be approved by the Department for prior to use.

Table 1033.01

Sampling and Testing Procedures	
Procedure	Method
Sampling	NDR T 2
Sieve Analysis	NDR T 27
Clay Lumps, Shale, and Soft Particles	NDR T 504
Abrasion	AASHTO T 96
Freeze and Thaw Soundness	NDR T 103
Specific Gravity and Absorption (course aggregate)	AASHTO T 85
Specific Gravity and Absorption (fine aggregate)	AASHTO T 84
Total Evaporable Moisture Content of Aggregates by Drying	AASHTO T 255
Plastic Fines in Graded Aggregates and Soils by Use of the Sand Equivalent Test	AASHTO T 176
Sodium Sulfate Soundness	AASHTO T 104
Calcium Carbonate	NDR C 25
Organic Impurities	AASHTO T 21
Mortar-Making Properties	AASHTO T 71
Reducing Field Samples of Aggregate to Testing Size	AASHTO T 248

2. Portland Cement Concrete Aggregates:**a. Sand-Gravel Aggregate:**

- (1) Aggregate shall be washed and composed of clean, hard, durable and uncoated particles.
- (2) Aggregates produced from wet pits by pumping must be adequately washed by means approved by the Department.
- (3) Aggregates from dry pits shall be adequately washed by means approved by the Department and have a Sand Equivalent value not less than 90 in accordance with AASTHO T 176.
 - (i) If the Sand Equivalent is less than 90, the Engineer may elect to stop aggregate production until such a time ASTM C 109 has been completed. The aggregate, when subjected to the test for mortar-making properties, shall produce a mortar having a compressive strength at the age of 7 days equal to or greater than that developed by mortar of the same proportions and consistency made of the same cement and aggregate after the aggregate has been washed to a sand equivalent greater than 90. Materials failing to produce equal or greater strength shall be unacceptable.

- (4) Aggregate for concrete shall have a soundness loss of not more than 10% by weight at the end of 5 cycles using Sodium Sulfate Soundness test AASHTO T 104.
- (5) The weight of the aggregate shall not contain more than 0.5% clay lumps.
- (6) Aggregate subjected to the colorimetric test for organic impurities which produces a color darker than the standard shall be further tested for its mortar-making properties in accordance with AASHTO T 71. The Engineer may elect to stop aggregate production until such a time AASHTO T 71 testing has been completed.
 - (i) Aggregate, when subjected to the test for mortar-making properties, shall produce a mortar having a compressive strength at the age of 7 days equal to or greater than that developed by mortar of the same proportions and consistency made of the same cement and aggregate after the aggregate has been treated in a 3% solution of sodium hydroxide. Materials failing to produce equal or greater strength shall be unacceptable, except when determined to be acceptable under the provisions of Subsection 105.03.
- (7) Aggregate shall meet the requirement in Tables 1033.02A, 1033.02B and 1033.03C.

Table 1033.02A

		Percentage	Percent Passing									
			1 1/2"	1"	3/4"	1/2"	3/8"	No.4	No.10	No.20	No.30	No.200
AGGREGATE SPECIFICATION RANGE	Class A	Max	--	--	--	--	100	100	90	--	40	3
		Min	--	--	--	--	100	92	64	--	10	0
	Class B	Max	--	100	--	--	--	97	70	--	40	3
		Min	--	100	--	--	--	77	50	--	16	0
	Class C	Max	--	100	--	--	--	88	50	--	20	3
		Min	--	100	--	--	--	44	24	--	4	0

Table 1033.02B

Aggregate Classes and Uses	
Aggregate Class	Concrete Description
A	Overlay Concrete SF
B	47BD, 47B-HE, 47B-OL, PR 1 and PR 3
C	BX

b. Ledge Rock Aggregate:

- (1) Aggregate shall consist of Limestone, Quartzite, Dolomite, Gravel and Granite composed of clean, hard, durable, and uncoated particles.
- (2) The percent of clay lumps, shale, or soft particles shall not exceed the following amounts:

Clay Lumps	0.5%
Shale	1.0%
Soft Particles	3.5%

- (3) Any combination of clay lumps, shale, and soft particles shall not exceed 3.5%.

- (4) Aggregate for concrete shall be free of coatings that will inhibit bond and free of injurious quantities of loam, alkali, organic matter, thin or laminated pieces, chert, or other deleterious substances as determined by the Engineer.
- (5) Aggregate for concrete shall not have a soundness loss greater than 8.0% by weight at the completion of 16 cycles of alternate freezing and thawing.
- (6) Aggregates for concrete shall have a Los Angeles Abrasion loss percentage of not more than 40.
- (7) All fractions passing the No.4 sieve shall meet quality requirement of soundness loss of not more than 10% by weight at the end of 5 cycles using sodium sulfate solution.
- (8) The ledge rock shall be tested according to ASTM C 1260.
 - (a) The mortar bars for the ASTM C 1260 shall not exceed 0.10% expansion at 28 days.
 - (i) If the proposed ledge rock exceeds 0.10% expansion at 28 days, the ledge rock shall be tested in accordance to ASTM C 1567. If the expansion is greater than 0.10%, the ledge aggregate shall not be used.
 - a. The ASTM C 1567 mortar bars shall be composed of Type IP or IT Interground/blended cement and the proposed Ledge Rock aggregate.
 - b. To accommodate precision within multi-laboratory testing, expansion up to and including 0.13% will be accepted for use. If the expansion is above 0.13%, the material is noncompliant.
- (9) Aggregate shall meet the requirements in Tables 1033.03A, B, and C.

Table 1033.03A

	Percent	Percent Passing										
		1 1/2"	1"	3/4"	1/2"	3/8"	No.4	No.10	No.20	No.30	No.200	
AGGREGATE SPECIFICATION RANGE	Class E	Max	100	100	90	--	45	12	--	*4	--	3
	Class E	Min	100	92	66	--	15	0	--	0	--	0
AGGREGATE SPECIFICATION RANGE	Class F	Max	--	--	100	100	90	30	8	--	--	3
	Class F	Min	--	--	100	96	40	4	0	--	--	0

*If the No. 200 sieve is less than 1.5% passing the No.20 sieve could be increased to maximum of 6% passing.

Table 1033.03B

Aggregate Classes and Uses	
Aggregate Class	Concrete Description
E	47BD, 47B-HE, PR 1 and PR 3
F	47B-OL, Overlay Concrete SF

c. Combined Aggregates:

- (1) The Contractor shall design and meet the specification requirements. It is the Contractor's responsibility to provide desirable mix properties; such as, but not limited to, workability, resistance to segregation, stable air void system, good finishing properties and good consolidation properties.
- (2) The combined blended aggregate shall meet the requirement in Table 1033.03C and 1033.03D.

Table 1033.03C

*Class R - Combined Aggregate Gradation Limits (Percent Passing)								
Sieve Size	1 ½ inch	1 inch	¾ inch	No.4	No.10	No.30	No. 50	No.200
Max	100	100	98.0	70.0	50.0	30.0	12.0	3.0
Min	-	92.0	85.0	45.0	31.0	8.0	2.0	0

* Refer to Subsection 1002.04, Paragraph 1.b.(8) for the traditional 47B Mix Design

Table 1033.03D

Aggregate Classes and Uses	
Aggregate Class	Concrete Description
R	47B

d. Aggregate Production and Testing:

- (1) Any change greater than 3% in the original verified constituent percentage of the combined aggregates gradation will be considered non-compliant. Any change of the combined gradation targets must remain within the Combined Aggregate Gradation Limits in Table 1033.03C. The Contractor shall resubmit a new mix design if the material is deemed non-compliant in accordance with Subsection 1002.04, Paragraph 1.
- (2) The blended gradation tolerance ranges from the approved mix design are established in Table 1033.03E.
 - (i) The Contractor shall assume the responsibility to cease operations when the specifications are not met. Production shall not be started again without the approval of the Engineer.

Table 1033.03E Blended Aggregate Production Tolerances

Sieve Size	Tolerances
No. 4 or greater	± 5%
No. 10 to No. 30	± 4%
No. 50	± 3%
Minus No. 200	± 1%

- (3) Ledge rock and aggregate from a dry pit shall be uniformly saturated with water before it is used. The wetting shall begin 24 hours before concrete mixing to allow complete saturation.

**DOWEL BARS
(J-15-0812)**

Paragraph 1.c. of Subsection 1022.01 in the Standard Specifications is void and superseded by the following:

1. c. Both Type A and Type B coated dowel bars shall be coated with a bond breaker shown on the NDR Approved Products List, dipped in asphalt or paraffin, or greased in accordance with the specified requirements as shown in the Standard Plans.

**EPOXY COATED REINFORCING STEEL
(J-15-0509)**

Paragraph 5. of Subsection 1021.03 in the Standard Specifications is void and superseded by the following:

5. In order to protect the coated reinforcement from damage, the Contractor shall use padded or nonmetallic slings and padded straps. Bundled bars shall be handled in a manner which will prevent excessive sagging of bars which will damage the coating. If circumstances require storing coated steel reinforcing bars outdoors for more than two months, protective storage measures shall be implemented to protect the material from sunlight, salt spray and weather exposure. Coated steel reinforcing bars, whether individual bars or bundles of bars, or both, shall be covered with opaque polyethylene sheeting or other suitable opaque protective material. For stacked bundles, the protective covering shall be draped around the perimeter of the stack. The covering shall be secured adequately, and allow for air circulation around the bars to minimize condensation under the covering. Coated steel reinforcing bars, whether individual bars or bundles of bars, or both, shall be stored off the ground on protective cribbing. The bundled bars shall not be dropped or dragged. If, in the opinion of the Engineer, the coated bars have been extensively damaged, the material will be rejected. The Contractor may propose, for the approval of the Engineer, alternate precautionary measures.

**PROPOSAL GUARANTY
(A-40-0307)**

As an evidence of good faith in submitting a bid for this work, the bidder shall indicate the type of bid bond applied to this project in accordance with the Proposal Guaranty Bid Bond Section of these Special Provisions.

* * * * *

600INFDEC14

INDEX

AGGREGATES86

BITUMINOUS LIQUID COMPOUNDS FOR CURING CONCRETE80

BORROW, WASTE, STOCKPILE, AND PLANT SITE APPROVAL 19

BUY AMERICA..... 18

CALCIUM CHLORIDE.....77

CONCRETE PAVEMENT REPAIR55

CONCRETE PROTECTION BARRIERS44

CONSTRUCTION DETAILS.....28

CONTRACT TIME ALLOWANCE 15

DEFORMED METAL CENTER JOINT AND METAL KEYWAY86

DOWEL BARS 91

EARTH SHOULDER CONSTRUCTION30

ENVIRONMENTAL COMMITMENT 10

EPOXY COATED REINFORCING STEEL.....91

EPOXY COMPOUNDS AND ADHESIVES85

EXCAVATION AND EMBANKMENT.....29

FUEL COST ADJUSTMENT PAYMENT28

GENERAL CONDITIONS..... 6

INERTIAL BARRIER SYSTEM36

JOINT AND CRACK SEALING FILLER80

LEGAL RELATIONS AND RESPONSIBILITY TO THE PUBLIC..... 14

LIABILITY INSURANCE25

LIQUID MEMBRANE-FORMING COMPOUNDS FOR CURING CONCRETE.....79

PARTIAL PAYMENT17

PORTLAND AND INTERGROUND/BLENDED CEMENT72

PORTLAND CEMENT CONCRETE.....64

PORTLAND CEMENT CONCRETE PAVEMENT SMOOTHNESS48

PROPOSAL GUARANTY91

PROPOSAL GUARANTY BID BOND.....13

RELOCATE INERTIAL BARRIER SYSTEM30

REQUIRED SUBCONTRACTOR/SUPPLIER QUOTATIONS LIST 13

RUMBLE STRIPS.....47

SECTION 1007 -- CHEMICAL ADMIXTURES.....77

SEEDING.....63

SHOP PLANS AND ELECTRONIC SHOP DRAWINGS24

SILICA FUME79

SPECIAL PROSECUTION AND PROGRESS

(Assessments).....9

(Federal Immigration Verification System) 15

(General Requirements).....7

(Holidays).....7

(Migratory Birds) 10

(Optional Concrete Protection Barriers)8

(Subletting or Assigning of Contract)20

STATUS OF RIGHT-OF-WAY.....7

STATUS OF UTILITIES.....6

STORM WATER DISCHARGES 12

SURVEILLANCE OF TEMPORARY TRAFFIC CONTROL DEVICES45

TEMPORARY PAVEMENT MARKING33

TEMPORARY TRAFFIC CONTROL DEVICES

(Type II Barricades, Reflectorized Drums, 42" (1070 mm) Reflective Cones, and Vertical Panels).....31

TEMPORARY TRAFFIC CONTROL FOR PERMANENT PAVEMENT MARKING35

TYPE B HIGH INTENSITY WARNING LIGHTS.....31

VALUE ENGINEERING PROPOSALS (VEP) 14

WATER.....29

WATER FOR CONCRETE76

WET REFLECTIVE POLYUREA PAVEMENT MARKING, GROOVED36

WORK ZONE TRAFFIC CONTROL SIGNS32

WORKER VISIBILITY 13

NEBRASKA DEPARTMENT OF ROADS

PAGE: 1
DATE: 10/24/14

SCHEDULE OF ITEMS

CONTRACT ID: 6975D

PROJECT(S): S-80-3(1058)

CALL ORDER NO. : 600

LINE NO	ITEM DESCRIPTION	APPROX. QUANTITY AND UNITS	UNIT PRICE		BID AMOUNT	
			DOLLARS	CTS	DOLLARS	CTS
SECTION 0001 GROUP 3 CONCRETE PAVEMENT						
0001	0001.00 SURVEILLANCE OF TEMPORARY TRAFFIC CONTROL DEVICES	153.000 CDAY	.		.	
0002	0001.08 BARRICADE, TYPE II	66000.000 BDAY	0.50000		33000.00	
0003	0001.10 BARRICADE, TYPE III	972.000 BDAY	.		.	
0004	0001.75 TEMPORARY SIGN DAY	720.000 EACH	.		.	
0005	0001.90 SIGN DAY	8749.000 EACH	.		.	
0006	0002.28 TEMPORARY PAVEMENT MARKING REMOVAL	47500.000 LF	.		.	
0007	0002.30 PAVEMENT MARKING REMOVAL	22500.000 LF	.		.	
0008	0002.44 TEMPORARY PAVEMENT MARKING, TYPE PAINT	50000.000 LF	.		.	
0009	0002.47 TEMPORARY PAVEMENT MARKING SURFACE PREPARATION	50000.000 LF	.		.	
0010	0002.97 FLASHING ARROW PANEL	360.000 DAY	.		.	

NEBRASKA DEPARTMENT OF ROADS

PAGE: 2
DATE: 10/24/14

SCHEDULE OF ITEMS

CONTRACT ID: 6975D

PROJECT(S): S-80-3(1058)

CALL ORDER NO. : 600

LINE NO	ITEM DESCRIPTION	APPROX. QUANTITY AND UNITS	UNIT PRICE		BID AMOUNT	
			DOLLARS	CTS	DOLLARS	CTS
0011	0003.50 CONCRETE PROTECTION BARRIER	3050.000 LF	.		.	
0012	0003.56 RELOCATE CONCRETE PROTECTION BARRIER	5255.000 LF	.		.	
0013	0003.57 RELOCATE INERTIAL BARRIER SYSTEM	7.000 EACH	.		.	
0014	0003.64 REPLACEMENT MODULE	18.000 EACH	.		.	
0015	0003.66 INERTIAL BARRIER SYSTEM	4.000 EACH	.		.	
0016	0030.30 MOBILIZATION	LUMP		LUMP		.
0017	1010.10 EXCAVATION, BORROW	10000.000 CY	.		.	
0018	3039.11 CONCRETE PAVEMENT REPAIR, TYPE A, FULL DEPTH	35.283 CY	.		.	
0019	3039.12 CONCRETE PAVEMENT REPAIR, TYPE B, FULL DEPTH	118.090 CY	.		.	
0020	3039.13 CONCRETE PAVEMENT REPAIR, TYPE C, FULL DEPTH	4685.204 CY	.		.	
0021	3300.50 PORTLAND CEMENT CONCRETE SMOOTHNESS TESTING	LUMP		LUMP		.

NEBRASKA DEPARTMENT OF ROADS

PAGE: 3
DATE: 10/24/14

SCHEDULE OF ITEMS

CONTRACT ID: 6975D

PROJECT(S): S-80-3(1058)

CALL ORDER NO. : 600

LINE NO	ITEM DESCRIPTION	APPROX. QUANTITY AND UNITS	UNIT PRICE		BID AMOUNT	
			DOLLARS	CTS	DOLLARS	CTS
0022	7515.03 5" BLACK POLYUREA PAVEMENT MARKING, GROOVED	29790.000 LF	.		.	
0023	7515.36 5" WHITE WET REFLECTIVE POLYUREA PAVEMENT MARKING, GROOVED	172700.000 LF	.		.	
0024	7515.38 12" WHITE WET REFLECTIVE POLYUREA PAVEMENT MARKING, GROOVED	6030.000 LF	.		.	
0025	7516.35 5" YELLOW WET REFLECTIVE POLYUREA PAVEMENT MARKING, GROOVED	138700.000 LF	.		.	
0026	8028.01 FOUNDATION COURSE REPLACEMENT	79.000 CY	.		.	
0027	9111.00 WATER	250.000 MGAL	.		.	
0028	9170.00 EARTH SHOULDER CONSTRUCTION	2252.000 STA	.		.	
0029	9185.77 RUMBLE STRIPS, CONCRETE	2328.737 STA	.		.	
0030	L001.02 SEEDING, TYPE B	40.000 ACRE	.		.	
0031	L032.75 MULCH	80.000 TON	.		.	
	SECTION 0001 TOTAL				.	

NEBRASKA DEPARTMENT OF ROADS

PAGE: 4
 DATE: 10/24/14

SCHEDULE OF ITEMS

CONTRACT ID: 6975D

PROJECT(S): S-80-3(1058)

CALL ORDER NO. : 600

LINE NO	ITEM DESCRIPTION	APPROX. QUANTITY AND UNITS	UNIT PRICE		BID AMOUNT	
			DOLLARS	CTS	DOLLARS	CTS
TOTAL BID						.